

# Technical data sheet



Product: 8067E

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: EINSEITIG

Download: 16.04.2026

## FLEXIBLE AIR SEALING TAPE 8067E FAST-F

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Flexible Air Sealing Tape 8067E

## FAST-F

### Product Data Sheet

Date: June 2016

Supersedes: October 2015

---

#### Product Description

3M™ Flexible Air Sealing Tape 8067E FAST-F is a self-adhered, waterproof flashing tape. This product has a unique acrylic pressure sensitive adhesive that aggressively sticks and stays stuck both at lower and higher application temperatures than traditional flashing tapes

---

#### Intended Use

- Seaming air of interior water vapour membranes
- Reparation of interior water vapour barriers
- Sealing around openings and joints in building applications
- Sealing around window and door installations
- Sealing of feedthroughs for cables
- Sealing around other wall interruptions in non-roof areas, such as thresholds, dryer vents and hose bibs. Taping seams aids in reducing air infiltration, improving the effectiveness of insulation and reducing heating and cooling costs.

---

#### Key Features

- Proprietary Film backing seals around nails and staples to prevent moisture intrusion
- Can be applied to materials without primers or staples and bonds
- Tough backing resists punctures and tears during application.
- High tack adhesive sticks and stays stuck to most common building materials.
- Adhesive provides an unusual combination of both cold and hot temperature adhesion to most substrates, which can extend the construction season in many climates.
- No adhesive melting or staining in summer heat.
- Unique backing is thin to fit conveniently into corners and under siding.
- Can be installed at temperatures as low as -20 °C and as warm as 50 °C
- Resists UV exposure up to 12 months
- Compatible with many building sealants: No adverse reaction with synthetic rubber, butyl, polyurethane, silicone and silane terminated hybrid sealants.
- Measurement markings for ease in cutting to the desired length

**Physical Properties**

Tape Colour	Tan
Tape Thickness (Film, Adhesive ) (ASTM D-3652)	0,270 mm ± 0,015 mm
Liner	0,170 mm ± 0,005mm
Backing	Proprietary Film
Release Liner	Heavy paper, split
Adhesive Type	Acrylic

**Performance Characteristics**

<b>Adhesion to Polished Steel</b> 90° peel @room temp, 24 hr dwell, jaw speed 300mm/min (ASTM D-3330)	88 N/100mm
<b>Adhesion Polyethylene</b> 90° peel @room temp, 24 hr dwell, jaw speed 300mm/min (ASTM D-3330)	70 N/100mm
<b>Adhesion to Aluminium</b> 90° peel @room temp, 24 hr dwell, jaw speed 300mm/min (ASTM D-3330)	110 N/100mm
<b>Tensile Properties</b> Longitudinal Transverse (acc. to EN 12311-, 100 mm/min)	135 N/50 mm / 1116 % 143 N/50 mm / 1240 %
<b>Thermal Shock Resistance</b> -20 °C up to 60 °C Ift Richtlinie MO-01/1 (4.3)	fulfilled
<b>Dynamic Shear Strength to different substrates</b> (acc. to EN 12311-, 5 mm/min)	30 – 47 kPa
<b>Light resistance and resistance to moisture penetration</b> Ift Richtlinie MO-01/1 (4.4)	fulfilled
<b>Water Penetration Around Nails</b> (ASTM 1970)	Pass
<b>Water Vapour Permeability (s<sub>d</sub> value)</b> (EN ISO 12572 : 2001-06) (A)	18,1 m
<b>Application Temperature Performance</b>	-20 °C up to 50 °C

---

### **Building Materials Compatibility Testing by “ift Rosenheim”**

The following building materials have been tested on compatibility (up to 60°C) with 3M™ Flexible Air Sealing Tape 8067E FAST-F by the scientific service provider and international testing institute “ift Rosenheim” with the result of no optical or function-affecting impairments

- Concrete C35
- Exterior plaster HASIT 650 cement mortar
- Interior plaster HASIT 150
- Building plaster with Weber light mortar LM21 without primer
- Building plaster with Weber light mortar LM21 with primer
- fibreC glass fibre concrete slab 2.0
- Wood (spruce) rough, grinded / varnished / painted
- OSB panels class 3 with rough surface
- PVC-U, white
- Anodised aluminium / Powder-coated aluminium
- Vapour barrier: Ampatex DB90
- Vapour barrier: Öko Natur vapour barrier (Isozell)
- Vapour barrier: Folag Starvap D2 (PO)
- Vapour barrier: Isover Vario KM (PA)
- Vapour barrier: Siga Majpell (PE)
- Vapour barrier: D-Tack Tacolau (Alu Coating surface)

---

### **Application Handling**

To obtain the best adhesion, 8067E FAST-F can be installed when outdoor temperatures range from -20 °C up to 50 °C over clean surfaces that are free from dirt and debris and have not absorbed water. Surfaces should be free of any damaged, unsupported areas, sharp protrusions or voids.

Adheres to most common building materials. For difficult to stick to surfaces, test flashing tape adhesion before application. Use 3M™ Hi-Strength 90 Spray Adhesive to prime the substrate as needed prior to applying the flashing tape.

To apply, peel back a few centimetres of one side of the split paper release liner to position the tape. Remove the liner while applying firm pressure to the flashing tape surface as it comes into contact with the building surface. Repeat this procedure with the remaining side of the paper release liner and tape. Using a roller apply sufficient pressure along the entire tape surface to ensure a continuous seal and to eliminate trapping air beneath the tape.

#### **Warning:**

The paper release liner is slippery and should not be walked on at any time. Discard the paper release liner in a designated container.

---

### **3<sup>rd</sup> Party Evaluation**

3M™ Flexible Air Sealing Tape 8067E has been evaluated by SITAC (SP Technical Research Institute of Sweden) and approved in accordance with the provisions of the following sections of Boverket Building Regulations (BBR): issued by the National Board of Housing, Building and Planning.

- Moisture, General
- Moisture, Safety
- Air Tightness (in combination with window installations)

---

**UV Durability**

When exposed to natural sunlight in Florida and Arizona and when exposed to accelerated aging conditions, the performance of 3M™ Flexible Air Sealing Tape 8067E FAST-F remains stable over an extended period. Based on these tests and performance observed in actual installations, 3M is confident in claiming that the tape will remain fully functional up to 12 months of exposure to sunlight.

---

**Storage & Shelf Life**

Store at 16 °C – 25 °C and 40-65 % relative humidity in its original box. The product can be stored up to 24 months after production.

**Note:** Product shall not be exposed to UV radiation during storage

---

**For Additional Information**

To request additional product information or to arrange for sales assistance, call.....

Address correspondence to: 3M

---

**Important Notice**

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---

3M is a trademark the 3M Company.

<b>3M United Kingdom Plc</b> <b>3M House</b> <b>28 Great Jackson Street</b> <b>Manchester</b> <b>M15 4PA</b>	<b>Product Information:</b>  <b>Tel 0870 60 800 50</b> <b>Fax 0870 60 700 99</b>	<b>3M Ireland Limited</b> <b>The Iveagh Building</b> <b>The Park,</b> <b>Carrickmines</b> <b>Dublin 18,</b> <b>Ireland</b>	<b>Customer Service :</b>  <b>Tel (01) 280 3555</b> <b>Fax (01) 280 3509</b>
--	---	---	---