

Technical data sheet



Product: CSA-NF

Manufacturer: PERMABOND ENGINEERING ADHESIVES

Product group: KLEBSTOFF

Article group: AKTIVATOR

Download: 02.05.2024

PERMABOND® CSA-NF

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

Features & Benefits

- Non-flammable
- Non-blooming
- Activates difficult or porous surfaces
- Improves adhesive gap fill

Description

Permabond[®] C Surface Activator (CSA-NF) is used in conjunction with Permabond cyanoacrylate adhesives to promote a faster cure and to extend their gap-filling capabilities. It significantly reduces the whitening effect often associated with more active cyanoacrylates. It has been developed to be non-harmful and non-flammable making storage, shipment and use of the product less hazardous.

Use of CSA-NF enables fillets of cured adhesive to be formed if required and can be used to reduce the effects of blooming, which can affect black or decorative surfaces. Also, it facilitates the bonding of porous surfaces.

Physical Properties

Colour	Colourless
Viscosity	1 mPa.s
Flashpoint	Non-flammable
Boiling Point	42°C
Specific Gravity	1.3

Storage & Handling

Storage Temperature	5 to 25°C (41 to 77°F)
---------------------	------------------------

Additional Information

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Material Safety Data Sheet.

Directions for Use

- Surfaces should be clean, dry and grease-free prior to primer application.
- Permabond CSA-NF should be applied either by wiping (using a clean cloth or brush), spraying or dipping one component.
- Allow CSA-NF to dry before assembling joint.
- Permabond cyanoacrylate adhesive is then applied to the untreated surface; the two parts should be quickly mated.
- Do not put the adhesive on the treated surface as the adhesive could cure before the parts can be properly mated. Only if the gap is extremely large (>0.5mm) activator may be applied to both surfaces.
- For maximum bond strength, allow adhesive to cure for 24 hours at 23°C.
- Permabond CSA-NF is formulated to minimise attack and maximise performance on certain plastics. However, it is recommended that the product is tested for compatibility prior to use in production.

For post-applying (e.g. for curing excess adhesive fillets or for wire tacking):

- Lightly spray or drip activator onto uncured adhesive (do not react large quantities).

Do not mix Permabond CSA-NF directly with cyanoacrylate adhesives.

Contact Permabond:

- Americas +1 732 868 1372
- US 800-640-7599
- Asia + 86 21 5773 4913
- Europe +44 (0) 1962 711661
- UK 0800 975 9800
- Deutschland 0800 111 388
- France 0805 111 388

info.americas@permabond.com

info.europe@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.