

# Technical data sheet



Product: NT-8511-P

Manufacturer: TMG SOLUTIONS

Product group: KLEBEBAND

Article group: EINSEITIG

Download: 06.05.2024

## NT-8511-P POLYESTER AND SILICONE TAPE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



## **NT-8511-P – POLYESTER AND SILICONE TAPE**

### **TECHNICAL DATA SHEET**

Temperature resistance	180°C (220°C short time)
Backing thickness	25 microns polyester film
Adhesive thickness	55 microns silicone adhesive
Total Thickness	80 microns
Breaking strength	5.2 kg per cm
Elongation	90%
Adhesion to steel	0.45kg per cm
Dielectric Strength	4300 volts

### **Product Information**

Our recommendations are made in good faith and are based on our experience with these products. Since the conditions of use of these products are beyond our control, this data is given on the express condition and understanding that TMG Solutions, S.L. will not be liable to any person by reason thereof. Nothing herein shall be deemed to be a recommendation to use any product in violation of any existing patent right.