

Technical data sheet



Product: POP

Manufacturer: PERMABOND ENGINEERING ADHESIVES

Product group: KLEBSTOFF

Article group: PRIMER

Download: 03.05.2024

PERMABOND® POLYOLEFIN PRIMER (POP)

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

Description

Permabond® Polyolefin Primer has been developed for surface treatment of polyolefins, PTFE and silicones prior to bonding with Permabond® Cyanoacrylate adhesives. Due to their low surface energy, plastics such as PTFE, Polypropylene (PP), Polyethylene (PE) and Silicones are difficult to bond without special surface treatment. However, after treatment with Permabond® Polyolefin Primer, durable bonds stronger than the substrate material can be achieved.

Biocompatibility

ISO 10993-5 Cytotoxicity

Physical Properties

Appearance	Colourless Liquid
Viscosity @ 25°C	0.6 mPa.s (cP)
Specific Gravity	0.7
Boiling Point	98°C
Flash Point	-4°C
Evaporation Rate	2.8 (butyl acetate = 1)
Drying Time @23°C	30 Seconds
UV-fluorescence	Yes

Storage & Handling

Storage Temperature	5 to 25°C (41 to 77°F)
---------------------	------------------------

Do not mix Permabond® POP directly with cyanoacrylate adhesives

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Safety Data Sheet.

Performance Properties

Substrate	Untreated	Treated with Primer
4mm Polypropylene bonded with 105	0.5 MPa Adhesive Failure	7.1 MPa Substrate Failure
4mm Polypropylene bonded with 2050	0.27 MPa Adhesive Failure	7.0 MPa Substrate Failure
2mm Polypropylene bonded with 105	0.11 MPa Adhesive Failure	3.5 MPa Substrate Failure
2mm Polypropylene bonded with 2050	0.15 MPa Adhesive Failure	3.4 MPa Substrate Failure
2mm Polyethylene bonded with 2050	0 MPa Adhesive Failure	2.7 MPa Substrate Failure
6mm PTFE to Mild Steel Bonded with 105	0 MPa Adhesive Failure	4.0 MPa Adhesive Failure

This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

Performance Properties

Polyolefin (PE, PP)	Significant improvement in bond strength
Silicone	Significant improvement in bond strength
Fluoropolymers (PTFE, FEP, PFA, ETFE)	Bond strength increasing
PBT, PMP, PPS, Polystyrene, Polyurethane	Significant improvement in bond strength
ABS	No improvement in bond strength
DAP, Polyamide	Strength may decrease

Directions for Use

- 1) Surfaces should be clean, dry and grease-free prior to primer application.
- 2) Permabond® POP should be applied only to the low energy surfaces by wiping (using a clean cloth or brush), dipping or spraying.
- 3) The components must be allowed to dry at ambient temperature prior to bonding.
- 4) For polyolefins, bonding with Permabond® cyanoacrylate adhesive can be performed up to 2 hours after POP treatment (this may be less depending on the particular blend of polyolefin). Immediate bonding is recommended for PTFE.
- 5) Handling time and cure speed will depend on the substrates and adhesive selected. (Handling time is the time from when the joint is assembled to the time when adequate strength has developed for the joint to be handled.)
- 6) For maximum bond strength, allow adhesive to cure for 24 hours at 23°C.

Permabond® POP is formulated to minimise attack and maximise performance on certain plastics. However, it is recommended that the product is tested for compatibility prior to use in production.

Video Links

Surface preparation:

<https://youtu.be/8CMOMP7hXjU>

POP Primer directions for use:

<https://youtu.be/G9yz8OqThJk>



www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.