## Technical data sheet



**Product:** 301

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: **KLEBEBAND** 

Article group: **EINSEITIG** 

Download: 15.12.2025

## PERFORMANCE MASKING TAPE 301E

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results



# **Performance Masking Tape 301E**

## **Product Data Sheet**

March 2018

Supersedes: September 2014

#### **Product Description**

3M<sup>™</sup> Performance Masking Tape 301E is a chamois coloured, latex saturated crepe paper coated with a rubber resin adhesive

#### **Key Features**

- A balanced product where its temperature performance allows air drying and oven curing of paint systems up to a maximum of 100 °C for 1 hour with clean and easy removal.
- Suitable for Infrared / UV curing.
- Good solvent and moisture resistance.
- Crepe paper backing for conformability that will maintain integrity when formed around corners.
- Backing saturated for easy tear resists slivering yet hand tearable.
- Rubber adhesive with instant adhesion.
- Good holding power that resists lifting or curling and helps reduce rework.
- Special back side treatment controls unwind and helps reduce waste
- Designed for indoor use only. Tape should not be subjected to outdoor exposure or prolonged periods of sunlight as product may become very difficult to remove.

#### **Physical Properties**

Adhesive Type	Rubber
Backing Type	Crepe paper
Tape Colour	Chamois

#### **Performance Characteristics**

Adhesion to Steel AFERA 5001	9 N/25mm
Tensile Strength AFERA 5004	95 N/25mm
Elongation at Break AFERA 5004	10 %
Thickness AFERA 5006	0.150 mm
Temperature Performance	100 °C for 1 hour

#### Storage & Shelf Life

Store at 16  $^{\circ}$ C - 25  $^{\circ}$ C and 40 - 65  $^{\circ}$ C relative humidity in its original box. The product can be stored up to 12 months after production.

#### For Additional Information

For additional product information, please go to <a href="www.3M.be/bonding">www.3M.be/bonding</a> or <a href="www.3M.nl/bonding">www.3M.nl/bonding</a>

#### **Important Notice**

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark the 3M Company.



Industrial Adhesives & Tapes Division 3M Belgium Hermeslaan 7 1831 Diegem Belgium Industrial Adhesives & Tapes Division 3M Nederland Molengraafsingel 29 2629 JD Delft Nederland