

# Technical data sheet



Product: 5320F

Manufacturer: NITTO BELGIUM N.V.

Product group: KLEBEBAND

Article group: DOPPELSEITIG

Download: 13.03.2025

## NITTO TR-5320F

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708

Double-coated adhesive tape

# TR-5320F


## Outline

Nitto Denko thermal conductive adhesive tape TR-5320F offers superior thermal conductive property by using the thermal conductive adhesive layer.

TR-5320F acquires flammability UL94 V-0 certification.

TR-5320F offers excellent workability and processability by adopting the polyester film as base material. The tape can be used various area such as electronics.

## Structure



## Features

- Superior thermal conductive property.
- Excellent adhesion and superior adhesive reliability.
- Flammability UL94 V-0[Halogen-free].[ file No.: QMFZ2.E52859 ].
- Excellent workability and processability.
- Ten restricted substances by RoHS are not contained.

## Applications

- Fixing of LED substrate to chassis
- Fixing of CPU to heat sink or heat radiation fan
- Fixing of various semiconductor packages to heat sinks
- Fixing of electronic components to heat radiation sheet

## Standard sizes

Tape thickness(mm)	Width(mm)	Length(m)
0.20	10~1000	20,50

For details, please contact us.

TR-5320F 10-P-0292\_E (1/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

**Properties**

- 180 degree peeling adhesion for each substrate

Substrate	TR-5320F
Stainless steel plate	11.2
Aluminum plate (A1050)	9.6
Aluminum plate (A6063)	12.2
Acrylic plate	13.1
Glass epoxy plate	16.9
Bakelite plate	18.9
Ceramics plate	13.5
White solder resist for LED	33.2

(Unit : N/20 mm)

Tape area : 20mm width

Lining material : PET film #25


Pressing condition : 1pass back and forth with 2-kg roller at 23 degree C/50%RH

Applying condition : 23 degree C/50%RH×30min

Peeling speed : 300 mm/min

Peeling angle : 180 degree

Measurement temperature : 23 degree C/50%RH



- 180 degree peeling adhesion –Aging(durability) at each condition after applying

Condition	TR-5320F
Initial(23 degree C/50%RH×30min)	11.2
23 degree C×42 days(1000hrs)	13.3
60 degree C×42 days(1000hrs)	16.8
100 degree C×42 days(1000hrs)	20.5
120 degree C×42 days(1000hrs)	24.1
85 degree C /85%RH×42 days(1000hrs)	24.0
Thermal shock[1000cycles] <sup>※1</sup>	21.8

(Unit : N/20 mm)

Substrate : Stainless steel plate

Lining material : PET film #25

Pressing condition : 1pass back and forth with 2-kg roller at 23 degree C/50%RH

Applying condition : Refer to the left table.

Peeling speed : 300 mm/min

Peeling angle : 180 degree

Measurement temperature : 23 degree C/50%RH

※ 1 : Thermal shock condition

[-40 degree C ×30min⇒125 degree C×30min⇒]  
×1000 cycles

TR-5320F 10-P-0292\_E (2/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

**Properties**

●Holding power

Temperature	TR-5320F
23 degree C	0.1
40 degree C	0.1
80 degree C	0.1
100 degree C	0.1

(Unit: mm/hr)

Substrate : Aluminum plate

Applying condition:

Measurement temperature x30min

Measurement temperature :


23 degree C, 40 degree C,

80 degree C, 100 degree C

Tape area : 10mm x 10mm

Load : 0.98N(100g)

Load time : 1hr



●Holding power -Aging(durability) at each condition after applying

Condition	TR-5320F
Initial (23 degree C/50%RH)	0.1
23 degree Cx42 days(1000hrs)	0.1
60 degree Cx42 days(1000hrs)	0.1
100 degree Cx42 days(1000hrs)	0.1
60 degree C /90%RHx42 days(1000hrs)	0.1
Thermal shock[1000cycles] <sup>※ 1</sup>	0.1

(Unit: mm/hr)

Substrate : Aluminum plate

Applying condition: Refer to the left table.

Measurement temperature : 40 degree C

Tape area : 10mm x 10 mm

Load : 0.98N(100g)

Load time : 1hr

※ 1 : Thermal shock condition

[-40 degree C x30min⇒125 degree Cx30min⇒]  
x1000 cycles

TR-5320F 10-P-0292\_E (3/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.


**Properties**

● Thermal conductivity

	TR-5320F
Thermal conductivity	0.7

(Unit : W/m·K)

Steady state heat flow method  
Tape area: 20mm×20mm  
Heat temperature : 80 degree C  
Cool temperature : 20 degree C  
Load : 250kPa



● Thermal resistance

	TR-5320F
Thermal resistance	3.3

(Unit : cm<sup>2</sup>·K/W)

Steady state heat flow method  
Tape area: 20mm×20mm  
Heat temperature : 80 degree C  
Cool temperature : 20 degree C  
Load : 250kPa


● Thermal conductivity -Aging(durability) at each condition after applying

Condition	TR-5320F
Initial(23 degree C/50%RH)	0.7
60 degree C×42 days(1000hrs)	0.7
100 degree C×42 days(1000hrs)	0.7
120 degree C×42 days(1000hrs)	0.7
85 degree C /85%RH×42 days(1000hrs)	0.7
Thermal shock[1000cycles] <sup>※1</sup>	0.7

(Unit : W/m·K)

Substrate : Aluminum plate  
Applying condition: Refer to the left table.  
Steady state heat flow method  
Tape area: 20mm×20mm  
Heat temperature : 80 degree C  
Cool temperature : 20 degree C  
Load : 250kPa

※1 : Thermal shock condition  
[-40 degree C ×30min  
⇒125 degree C×30min⇒]  
×1000 cycles



● Thermal resistance -Aging(durability) at each condition after applying

Condition	TR-5320F
Initial(23 degree C/50%RH)	3.3
60 degree C×42 days(1000hrs)	3.3
100 degree C×42 days(1000hrs)	3.4
120 degree C×42 days(1000hrs)	3.3
85 degree C /85%RH×42 days(1000hrs)	3.2
Thermal shock[1000cycles] <sup>※1</sup>	3.5

(Unit : cm<sup>2</sup>·K/W)

Substrate : Aluminum plate  
Applying condition: Refer to the left table.  
Steady state heat flow method  
Tape area: 20mm×20mm  
Heat temperature : 80 degree C  
Cool temperature : 20 degree C  
Load : 250kPa

※1 : Thermal shock condition  
[-40 degree C ×30min⇒125 degree C×30min⇒]  
×1000 cycles

TR-5320F 10-P-0292\_E (4/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

**Properties**

---

●Flammability

	<b>TR-5320F</b>
UL94	V-0 QMFZ2 E52859

(Unit : -)

Measurement condition : Refer to UL94 V test

●Electrical insulating property

	<b>TR-5320F</b>
Breakdown voltage	8.9

(Unit : kV)

Measurement temperature : 23 degree C

Measurement humidity : 50%RH

Voltage rising rate : 1kV/s

Load : 4.9N

●Total VOC emission

<b>Condition</b>	<b>TR-5320F</b>
80 degree C×0.5 hrs	40
130 degree C×0.5 hrs	100

(Unit : μg/g)

Tape area:5cm<sup>2</sup>

Applying condition: Refer to the left table.

Heating method: 20mL vial bottle

Measurement : Quantity of volatile gas 1mL

TR-5320F 10-P-0292\_E (5/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

## Precautions when using

---

- Remove all oil, moisture and dirt from the surface of the substrate before applying.
- The tape employs pressure-sensitive adhesive. Be sure to apply pressure with a roller or press when applying. Failure to do so could affect properties or appearance.
- The tape may not adhere well to significantly uneven or distorted surfaces. Level off the surface as much as possible before applying.
- Avoid setting or using such that significant stress is placed on the tape for several hours after application.

## Precautions when storing

---

- Be sure to keep the tape in its box when not using.
- Keep in a cool dark place not exposed to direct sunlight.

## Safety Precautions

WARNING
<ul style="list-style-type: none"><li>● Make sure the product is suitable for the application (objective and conditions) before attempting to use. The tape may come off depending on the substrate to or conditions under which it is applied.</li><li>● Use in combination with another method of joining if there is possibility of an accident.</li></ul>



Published in March 2019

TR-5320F 10-P-0292\_E (6/6)

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.