

Technical data sheet



Product: 7266

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: 2-K KLEBSTOFF

Download: 26.12.2024

3M™ SCOTCH-WELD™ EC-7266 B/A

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

3M™ Scotch-Weld™ EC-7266 B/A

Two Part Structural Adhesive

Product Description

3M™ Scotch-Weld™ Structural Adhesive EC-7266 B/A is a two component epoxy paste adhesive which cures at room temperature or with mild heat to form a tough, impact resistant structural bond. It has an excellent adhesion to a wide variety of substrates such as metals, glass, ceramics and plastics, incl. GFRP and CFRP. Once cured, it provides extremely high shear and peel strength over a wide temperature range, with outstanding resistance to harsh environments and chemicals commonly encountered in aerospace applications.

Key Features

- EN 9100 certified Aircraft interior bonding adhesive
- Toughened system providing extremely high shear and peel strength
- Available in duo-pack cartridges

Product Characterization

The following technical information and data should be considered representative or typical only and should not be used for specification purpose

General Properties	Part B	Part A
Colour	Off-white	Clear Yellow
Base	Modified epoxy	Modified amine
Consistency	Paste	Paste
Density	1.12 g / cm ³	1.07 g / cm ³
Solids	100 %	100 %
Viscosity 23 ± 2 °C ^(a)	80 Pas	10 Pas
Mix ratio by volume (by weight)	2 : 1 by vol. (2 : 0,96 by wt.)	
Work life at 23 ± 2 °C ^(b)	60 minutes	
Strength build-up at 23 ± 2 °C		
Handling strength at 23 ± 2 °C ^(c)	3-4 hours	
Full cure cycle	7 days at room temperature, or 2 hours at 65 °C	
Packaging	Duo pack cartridges and pails	

^(a) Brookfield RVF Spindle 6, 10 rpm

^(b) 50 g of mixed adhesive

^(c) Time to reach > 1 MPa Overlap Shear Strength

Product Performance

The following data show typical values obtained with Scotch-Weld™ EC-7266 B/A on unprimed, sulfochromic etched, clad 2024 T3 aluminium. The samples have been cured for 7 days at room temperature, if not stated otherwise. To control the bond line thickness, approximately 1 wt. % of glass beads, 90 – 150 µm diameter, were added to the adhesive.

Mechanical Properties		Test Temperature	Cured for 7 days at 23 °C	Cured for 2 hours at 65 °C
Overlap Shear Strength EN 2243-1		-55 °C	31 MPa	40 MPa
		23 °C	31 MPa	35 MPa
		85 °C	5 MPa	10 MPa
Overlap Shear Strength EN 2243-1	Stainless steel	23 °C	-	28 MPa
	ABS	23 °C	4 MPa	-
	PMMA	23 °C	2 MPa	-
Floating Roller Peel Strength EN 2243-2		-55 °C	150 N / 25 mm	-
		23 °C	250 N / 25 mm	-
		85 °C	90 N / 25 mm	-

Handling, Application, Storage

Precautionary Information

Refer to product label and Material Safety Data Sheet (MSDS) for health and safety information before using this product. For MSDS visit our website www.3M.com/msds.

Instructions for use

While this information is provided as general application guideline based upon typical conditions, it is recognized that no two applications are identical due to, among other things, differing assemblies, methods of heat and pressure application, production equipment and other limitations. It is therefore suggested that experiments be run, within the actual constraints imposed to determine optimum conditions for your specific application and to determine suitability of product for the particular intended use.

Process step	Instruction
Surface preparation	<p>The strength and durability of a bonded joint are dependent on proper treatment of the surface to be bonded. An acclimated, thoroughly cleaned, dry, grease-free surface is essential for maximum performance. Cleaning methods which will produce a break free water film on metal surfaces are generally satisfactory.</p> <p>At the very least, joint surfaces should be cleaned with a good proprietary degreasing agent and mechanically abraded, e.g. with 3M Scotch-Brite™ 7447. Abrading should be followed by a second degreasing treatment, e.g. with 3M 08984 Adhesive Cleaner.</p> <p>Optimum processing temperature for substrates and adhesive is around room temperature of 23 °C.</p>

Process step	Instruction
Application	<p>This product consists of two parts. Combine Part B and Part A in a separate container just prior to application in the proportions specified. Note: Mix ratio deviations above +/- 5 % have significant influence on material performance. Mix both components thoroughly until a uniform colour is obtained. Apply adhesive to parts to be bonded before the work life expires, e.g. by spatula. Note: Work life depends to some extent on mixed quantity and the shape of the container. Use of a shallow container will minimize the quantity impact. In order to obtain optimum mechanical performance, the joint components should be assembled and clamped as soon as the adhesive has been applied and before end of the work life. A fixation of the joint and an even contact pressure throughout the joint area during cure will ensure optimum performance. Maximum shear strength is obtained with 0.10 – 0.20 mm bond line thickness. Close the containers after use to protect the material against humidity.</p>
Curing	<p>Once mixed, Scotch-Weld™ EC-7266 B/A will gel in approx. 2 hours, build up handling strength in 3-4 hours and fully cure within 7 days at room temperature. Note: Lower temperature will slow down the reaction times. Curing time can be accelerated by mild heat. Following times and temperatures will result in a full cure:</p> <ul style="list-style-type: none"> ▪ 7 days at 23 ± 2 °C ▪ 2 hours at 65 ± 2 °C <p>Note: The curing temperature may have influence on the final product performance.</p>
Cleaning	<p>Excess uncured adhesive can be cleaned with ketone type solvents. After cure the adhesive can be removed mechanically. Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and instructions for use.</p>
Storage and Handling	<p>Store the product at room temperature. Shelf life is minimum 12 months from date of shipment in the original unopened containers. The specific expiry date is mentioned on the product label.</p>

Important notice: All statements, technical information and recommendations in this data sheet are based on tests 3M believes to be reliable, but the accuracy or completeness of those tests is not guaranteed. All technical data and information should be considered typical or representative only and should not be used for specification purposes. Given the variety of factors that affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product before use to determine the suitability of the 3M product for the intended use and method of application. All questions of liability relating to the 3M product are governed by the terms of the sale subject to, where applicable, the prevailing law.



Automotive and Aerospace Solutions Division
European Aerospace Laboratory

www.3m.eu/aerospace
Reference: 227

© 3M 2017. All rights reserved.