Technical data sheet



Product:	MAX REPAIR
Manufacturer:	UHU GMBH & CO KG
Product group:	KLEBSTOFF
Article group:	KLEBSTOFF
Download:	30.06.2025

# **UHU MAX REPAIR POWER 20G**

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH Industriestraße 15 D-75382 Althengstett Telephone: E-Mail: +49(0)7051/9297-0 Website: +49(0)7051/9297-99 www.tewipack.de

Fax

info@tewipack.de

Managing director: Alexander Uhl, Michael Uhl HRB 330424 Calw Amtsgericht Stuttgart 85

Bank details: Sparkasse Pforzheim BLZ 666 500 Konto 17 787

Commerzbank Sindelfingen BLZ 603 400 71 Konto 8 001 166

Vereinigte Volksbank AG Böblingen BLZ 603 900 00 Konto 80 089 003

Postbank Stuttgart BLZ 600 100 70 Konto 146 294 708



# **MAX REPAIR POWER** POWERFUL AND FLEXIBLE REPAIR ADHESIVE FOR LONG LASTING REPAIR RESULTS



## APPLICATION

**Directions for use:** 

Can be applied directly from the tube using the fine dispensing nozzle.

Apply the adhesive on one side. Press the parts against each other. Adjustments can be made within 5 minutes. The maximum final bonding strength is reached after approximately 24 hours. **Stains/residue:** Use white spirit for removing wet adhesive residue. Dry adhesive residue can only be removed mechanically.

**Advice:** Loosen the stuck cap under the hot tap and remove any hardened adhesive in the tube cap with a sharp knife. After use, let some adhesive come out of the tube before you screw the cap on it.

### **PRODUCT DESCRIPTION**

MAX REPAIR POWER is a powerful and flexible repair adhesive for long lasting results of all sorts of repairs on porous and nonporous materials. Suitable for indoor and outdoor applications.

#### FIELD OF APPLICATION

Suitable for repairing porous and non-porous materials such as wood, textile, leather, cork, metal, glass, plastic, rubber, ceramic tiles, stone, cement and many other materials. Suitable for indoors and outdoors.

Not suitable for Polypropylene (PP), Polyethylene (PE) and P.T.F.E.

#### PROPERTIES

- · Extremely strong
- · Extremely flexible
- · Water resistant
- · Gap filling
- Dishwasher-safe
- · Resistant to shock and vibrations
- · Temperature resistant
- · UV resistant
- · Acid and solvent-free
- Transparent

#### PREPARATION

**Working Conditions:** The materials to be bonded must be clean, dry, free of dust and grease.

**Surface Requirements:** The surface must be dry, clean and free of dust and grease.

**Preliminary Surface Treatment:** Surfaces must be clean, dry and free from dust and grease.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

### 64636 - UHU MAX REPAIR POWER BLISTER 20 G DE/FR/IT

# UHU

# **MAX REPAIR POWER** POWERFUL AND FLEXIBLE REPAIR ADHESIVE FOR LONG LASTING REPAIR RESULTS

## TECHNICAL SPECIFICATIONS

Bonding technique:1-Sided applicationChemical base:SMP PolymerChemicals resistance:GoodColour:TransparentCure rate:1 mm/24hDensity approx.:1.1 g/cm³Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:10-15 minutesPaintability:GoodShear strength:5 minutesSolid matter approx.:100 %Solid matter approx.:100 %Vircesitance:YesUV resistance:YesUV resistance:YesUV resistance:Very goodVater resistance:Yery good	TECHNICAL SPECIFICATIONS	
Chemicals resistance:GoodColour:TransparentCure rate:1 mm/24hDensity approx.:1.1 g/cm³Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMoximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:YesUV resistance:Thixotropic	Bonding technique:	1-Sided application
Colour:TransparentCure rate:1 mm/24hDensity approx.:1.1 g/cm³Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:YesUV resistance:GoodViscosity:Thixotropic	Chemical base:	SMP Polymer
Cure rate:1 mm/24hDensity approx.:1.1 g/cm³Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Solid matter approx.:100 %Solvent free:YesUV resistance:YesUV resistance:Thixotropic	Chemicals resistance:	Good
Density approx.:1.1 g/cm³Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:YesUV resistance:FoodViscosity:Thixotropic	Colour:	Transparent
Elasticity:LimitedFilling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:YesUV resistance:Good	Cure rate:	1 mm/24h
Filling capacity:Very goodFinal bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:YesViscosity:Thixotropic	Density approx.:	1.1 g/cm <sup>3</sup>
Final bond strength:800 N/cm²Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Solvent free:YesUV resistance:YesUV resistance:GoodViscosity:Thixotropic	Elasticity:	Limited
Final bond strength after:24 hours. This might vary, based on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Solvent free:YesUV resistance:YesUV resistance:GoodViscosity:Thixotropic	Filling capacity:	Very good
on circumstances, like materials, temperature and humidity.Hardness (Shore A):80Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Solid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Final bond strength:	800 N/cm <sup>2</sup>
Initial Bonding after:10 minutes. This might vary, based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:5 minutesSolid matter approx.:100 %Solid matter approx.:100 %Vv resistance:YesUV resistance:GoodViscosity:Thixotropic	Final bond strength after:	on circumstances, like materials,
based on circumstances, like materials, temperature and humidity.Minimum temperature resistance:-40 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %UV resistance:YesUV resistance:GoodViscosity:Thixotropic	Hardness (Shore A):	80
resistance:120 °CMaximum temperature resistance:120 °CMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Initial Bonding after:	based on circumstances, like materials, temperature and
resistance:Very goodMoisture resistance:Very goodOpen time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic		-40 °C
Open time approx.:10-15 minutesPaintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic		120 °C
Paintability:GoodShear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Moisture resistance:	Very good
Shear strength:800 N/cm²Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Open time approx.:	10-15 minutes
Skinover time:5 minutesSolid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Paintability:	Good
Solid matter approx.:100 %Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Shear strength:	800 N/cm <sup>2</sup>
Solvent free:YesUV resistance:GoodViscosity:Thixotropic	Skinover time:	5 minutes
UV resistance:GoodViscosity:Thixotropic	Solid matter approx.:	100 %
Viscosity: Thixotropic	Solvent free:	Yes
	UV resistance:	Good
Water resistance: Very good	Viscosity:	Thixotropic
	Water resistance:	Very good

#### **PACK SIZES**

8 g, 20 g

#### **STORAGE CONDITIONS**

At least 24 months after date of manufacture. Limited shelf life after opening. Store in tightly closed packaging in a dry, cool and frost-free place.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.