

Technical data sheet



Product: 9720

Manufacturer: H.B. FULLER

Product group: KLEBSTOFF

Article group: SPRAY

Download: 10.07.2025

SWIFT®COL 9720

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

Swift[®]col 9720

Type of Adhesive

Spray adhesive.

Product Benefits

- for contact and one sided bonding
- quick initial adhesion
- uniform coat
- low odour
- transparent
- free from FCHC and CHC

Typical Applications

This product is suitable for bonding various materials with themselves and among one another.

Suitable substrates

Foam materials, jute, felt, textiles, insulating materials, polystyrene foam, leather, synthetic leather, several plastics and plastic foils, paper, cardboard, particle board, etc.

Typical Properties

Property	Value
Base	synthetic rubber
Colour	yellow
Density at 20°C	0,78 g/cm ³
Viscosity (Brookfield, Sp3, 100rpm, at 20°C)	350 mPa.s
Shelf life	12 months



H.B. Fuller



TECHNICAL DATA SHEET

Application Instructions

Bonding/Open time with one sided application: approx. 30 – 90 seconds

Contact life with two-sided application: approx. 1 – 15 minutes

Heat resistance: maximum 60°C, depending on stress

Shake can well before use!

The necessary spray width can be adjusted with a special outlet valve. Nozzle to be pressed downwards strongly and adhesive to be applied in an even coat. Spray distance should be 15 – 20 cm. Depending on particular requirements the spray adhesive can be used in one-sided application or in contact bonding. Parts to be fixed are sprayed one-sided and pressed together after 30 seconds. For bonding under high pressure, apply adhesive to both parts and press together within the contact life after a pre-drying time of approx. 1 minute.

Remarks:

When bonding polystyrene foam with itself or to impermeable materials, please make sure that no solvents are encircled. Special care should be given to low amount of adhesive and sufficient spray distance!

Important:

After use, spray can upside-down till propellant comes off in order to avoid drying up and clogging of nozzle.

Cleaning Instructions

Please contact your local Sales Office for available cleaning solutions.

Typical Packaging

Please contact your local Sales Office for available packaging options.

Storage Conditions

In original sealed packaging protected from sun, dust, moisture and high temperatures. Clean and dry conditions above +10°C and below +35°C.

Disposal Advice

Please refer to the MSDS for disposal instructions.

Safety Advice

Please refer to the MSDS for safety advice.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.



H.B. Fuller

H.B. Fuller Company

info-europe@hbfuller.com
www.hbfuller.com/
eimea/contact-us