

# Technical data sheet



Product: 2214

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: 1-K KLEBSTOFF

Download: 17.04.2026

## 3M™ SCOTCH-WELD™ 2214 REGULAR

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Adhesive 2214  
Regular



[Product Details](#)



[Regulatory Info/SDS](#)

## **Product Description**

3M™ Scotch-Weld™ one part epoxy adhesive 2214C that offer excellent shear, peel, and impact performance. These toughened products provide improved adhesion to many plastics and metals. These durable products provides structural strength.

## **Product Features**

- Toughened Paste
- Excellent shear strength
- one part
- High temperature resistance
- Excellent bonding strength
- Excellent aging performance

**Note:** Unless otherwise indicated, all properties measured at 72°F (22°C).

## **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## **Typical Uncured Physical Properties**

Attribute Name	Value
Color	Gray <sup>1</sup>
Viscosity	>1,000,000 cP <sup>2</sup>
Viscosity	60 to 200 s <sup>3</sup>
Net Weight	12 lb/gal
Components	1-Part
Base	Modified Epoxy

<sup>1</sup> Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.

<sup>2</sup> Because of Thixotropic paste nature of these products Brookfield viscosity will be over 1,000,000 cps.

<sup>3</sup> Time to deliver 20 gms@ 50 psi thru a 0.10in orifice

## **Typical Mixed Physical Properties**

Temperature: 121 °C (250 °F)

Attribute Name	Value
Time to Full Cure	40 min

## **Typical Physical Properties**

Attribute Name	Value
Cured Color	Gray

## Typical Cured Characteristics

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Value
Modulus		750,000 lb/in <sup>2</sup>
Shore D Hardness	ASTM D2240	85

## Typical Performance Characteristics

### Overlap Shear Strength

Surface Prep: MEK/Abrade/MEK

Temperature: 22 °C (72 °F)

Dwell Time: 7 d

Test Method: ASTM D1002

Substrate	Value
Aluminum	3,190 lb/in <sup>2</sup> <sup>1</sup>
Cold Rolled Steel	2,500 lb/in <sup>2</sup> <sup>1</sup>

<sup>1</sup> 1" wide 1/2" overlap samples, 1" x 4" substrates, bondline thickness 0.005-0.008in  
 Separation rate 0.1in/min metal, 2in/min plastic, 20in/min rubber.  
 Substrate thickness: steel 0.060in, other metal 0.05-0.064in, rubber 0.125in, plastic 0.125in  
 Cohesive Failure (CF), Adhesive Failure (AF), Substrate Failure (SF)

### T-Peel Adhesion

Temperature: 22 °C (72 °F)

Test Method: ASTM D1876

Substrate	Surface Prep	Value
Aluminum		5 lb/in width <sup>1</sup>
Steel	MEK wipe	50 lb/in width <sup>2</sup>

<sup>1</sup> T-Peel bonds were measured on 1 in. wide specimens cut from two FPL etched 8 in. x 8 in. x .032 in., 2024 T3 clad aluminum panels bonded together. The separation note of the testing jaws was 20 in./minute.  
<sup>2</sup> T-Peel bonds were measured on two 1" wide x 8" long specimens bonded together. After bonding they were then pulled apart in 180° Peel at a jaw separation rate of 20"/minute rate.

Attribute Name	Value
Elongation at Break	<2 %
Tensile Strength at Break	10,000 lb/in <sup>2</sup>

## Electrical and Thermal Properties

Attribute Name	Test Condition	Value
Coefficient of Thermal Expansion	0°C to 80°C	49 x 10 <sup>-6</sup> m/m/°C
Thermal Conductivity		0.231 (btu-ft)/(h-ft <sup>2</sup> -°F)

Attribute Name	Test Method	Value
Arc Resistance	ASTM D495	76 s

## Handling/Application Information

### Directions for Use

- 1.;Storage at 4°C
- 2.;Warm products to room temperature before opening containers to restore proper application consistency and to prevent moisture condensation on adhesive surface. Containers may be stored at room temperature for 1-2 hours to thaw. Do not warm at temperatures above 27°C.
- 3.;Use glove to avoid contacting container directly.
- 4.;Avoid freezing products again after warming

## Surface Preparation

3M™ Scotch-Weld™ Epoxy Adhesives are designed to be used on painted or coated metals, most plastics, glass, and some bare metals. The following cleaning methods are suggested for common surfaces:

Painted/coated metals:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.\*
2. Sandblast or lightly abrade using clean fine grit abrasives. Do not completely remove the paint layer or coating down to bare steel.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.\*

Aluminum/stainless steel:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.\*
2. Sandblast or lightly abrade using clean fine grit abrasives.
3. Wipe again with clean cloth and pure acetone to remove loose particles.\*

### Plastics:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.\*
2. Lightly abrade using fine grit abrasives.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.\*

### Glass:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.\*
2. Apply a thin coating of silane adhesion promoter to the glass surface and allow to dry completely before adhesive bonding.

\*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

## Application Equipment

These products may be applied by spatula, trowel, or flow equipment.

Dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to most applications. For more information, contact your local 3M sales representative.

**Note:** Minimum pumping temperature is 65°F (18°C) for all products.

3M™ Scotch-Weld™ Epoxy Adhesive 2214 Regular Production Extrusion Equipment

- Pump: Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7in<sup>3</sup> cycle
- Ram: Pneumatic type capacity-12 psi on material surface
- Hose: Super high pressure with standard lining
- Flow Gun: High pressure type

Output based on 1/4 in tip flow gun (material temperature 65°F [18°C]) (minimum pumping temperature is 65°F [18°C])

Hose Assembly Material Pressure (psi) (Output lb/min)

Length-20', I.D.-1/2 in 4800\* .36

Length-20', I.D.-3/4 in 4800\* 1.0

3M™ Scotch-Weld™ Epoxy Adhesive 2214 Non-Metallic Filled Production Extrusion Equipment

- Pump: Ratio 38:1 with a chopping check valve and priming piston
- Ram: Pneumatic type capacity-10 psi on material surface
- Hose: Super high pressure with standard lining
- Flow Gun: High pressure type

Output based on 1/4 in tip flow gun (material temperature 65°F [18°C]) (minimum pumping temperature is 65°F [18°C])

Hose Assembly Material Pressure (psi) (Output lb/min)

Length-10', I.D.-3/4 in 3000 2.3

Length-20', I.D.-3/4 in 3000 1.6

Length-20', I.D.-3/4 in

+10, I.D.-1/2 in 3000 1.2

Length-20', I.D.-1/2 in 3000 0.84

3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Temp Production Extrusion Equipment

- Pump: Ratio 40:1 with a chopping check valve and priming piston, 6 in. air motor. 2in<sup>3</sup>/cycle
- Ram: Pneumatic type capacity-12 psi on material surface
- Hose: Super high pressure with standard lining
- Flow Gun: High pressure type

Output based on 1/4 in tip flow gun (material temperature 65°F [18°C])

Hose Assembly Material Pressure (psi) (Output lb/min)

Length-20', I.D.-1/2 in 2400 0.4

Length-20', I.D.-3/4 in 2400 1.1

- 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Dense Production Extrusion Equipment
- Pump: Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7in<sup>3</sup>/cycle
  - Ram: Pneumatic type capacity-12 psi on material surface
  - Hose: Super high pressure with standard lining
  - Flow Gun: High pressure type

Output based on 1/4 in tip flow gun (material temperature 65°F [18°C]) (minimum pumping temperature is 65°F [18°C])  
Hose Assembly Material Pressure (psi) (Output lb/min)  
Length-20', I.D.-1/2 in 4500\* 0.45  
Length-20', I.D.-3/4 in 4500\* 0.9

- 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Temp New Formula Production Extrusion Equipment
- Pump: Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7in<sup>3</sup>/cycle
  - Ram: Pneumatic type capacity-12 psi on material surface
  - Hose: Super high pressure with standard lining
  - Flow Gun: High pressure type

Output based on 1/4 in tip flow gun (material temperature 65°F [18°C]) (minimum pumping temperature is 65°F [18°C])  
Hose Assembly Material Pressure (psi) (Output lb/min)  
Length-20', I.D.-1/2 in 4800\* 0.36  
Length-20', I.D.-3/4 in 4800\* 1.0

\*These pressures will require a special consideration during hose selection. They are actual working pressures.

## **Industry Specifications**

UL 94 HB

## **Storage and Shelf Life**

For maximum shelf life, store Duo-Pak cartridges and bulk containers at 32°F (0°C) to 40°F (4°C). Do not freeze. When stored at the recommended temperatures in the original unopened containers, this product has a shelf life of 12 months from date of manufacture when in cartridges, and 6 months from date of manufacture in bulk pails.

## **Precautionary Information**

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

## **Automotive Disclaimer**

**Select Automotive Applications:** This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M  
Electronics Device Bonding  
3M Center, Building 225-35-06  
St. Paul, MN 55144-1000  
800-362-3550  
877-369-2923 (Fax)  
www.3M.com

3M is a trademark of 3M Company  
©3M 2023 (6/23)