Technical data sheet



Product:	2011
Manufacturer:	H.B. FULLER
Product group:	KLEBSTOFF
Article group:	CYANACRYLAT
Download:	10.07.2025

CYBERBOND 2011

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH Industriestraße 15 D-75382 Althengstett

Telephone: E-Mail: +49(0)7051/9297-0 Fax +49(0)7051/9297-99 www.tewipack.de

info@tewipack.de Website:

Managing director: Alexander Uhl, Michael Uhl HRB 330424 Amtsgericht Stuttgart

Bank details: Sparkasse Pforzheim Calw BLZ 666 500 85 Konto 17 787 Commerzbank Sindelfingen BLZ 603 400 71 Konto 8 001 166

Vereinigte Volksbank AG Böblingen BLZ 603 900 00 Konto 80 089 003

Postbank Stuttgart BLZ 600 100 70 Konto 146 294 708



Cyberbond 2011

General Properties	Technology/Base	Ethyl-2-cyanoacrylate
	Type of Product	Adhesive
	Curing	Moisture curing
	Mechanical Properties	Semi-structural
	Colour	Transparent
	Product Series	Elastomer and Plastic Series
	Product Benefits	Fast bonding

Typical Technical Data

General

Physical Properties		
Density	1.05 g/cm ³	
Flash Point	82.5 °C	
Processing Guidelines and Parameters		
Shelf Life	12 months	unopened, < 20 °C
Viscosity	65 mPa⋅s to 200 mPa⋅s	158 1/s, cone-plate, 20 °C
Setting Time	20 s to 50 s	steel
Setting Time	2 s to 4 s	EPDM
Setting Time	2 s to 4 s	acrylonitrile butadiene styrene (ABS)
Service Conditions		
Service Temperature	-55 °C to 95 °C	
Solvent Resistance		
Alcohol	+++	e.g. Ethanol, Methanol, Isopropanol
Aliphatic hydrocarbons (alkanes)	++-	e.g. Petrol, Heptanes, Hexane
Aromatic hydrocarbons	++-	e.g. Benzyl, Toluol, Xylol
Ester (aliphatic)		e.g. Ethylacetate
Halogenated hydrocarbons		e.g. Methylenchloride, Chloroform, Chlorobenzol
Ketone		e.g. Acetone, Benzophenone
Weak aqueous acid	+++	e.g. diluted nitrite, muriatic acid, sulphuric acid, phosphoric acid
Concentrated Acid		e.g. nitric acid, muriatic acid, sulfic acid, phosphoric acid
Weak aqueous base	+++	e.g. diluted sodium hydroxide solution, caustic potash solution
Concentrated Base		e.g. sodium hydroxide solution, caustic potash solution
Water	++-	





Figure 1: Strength of Cured Adhesive



Figure 2: Hot Strength (%RT strength, tested at temperature)





Figure 3: Time Until Full Cure



Figure 4: Heat Ageing on Steel (aged at temp. indicated and tested @ 20°C)





Figure 5: Durability after Alternating Climate Storage



Product Properties

Applications	Fields of Application	Assembly and repair
		Electronics
		Automotive
		Construction
		Industrial assembly
		Transportation
Processing	Suitable Substrates	Various galvanized steels
		Various aluminium alloys
		Various steel alloys
		Various plastic substrates
		EPDM
		Various elastomeric materials
		Various other substrates
	Consistency	Medium viscosity
		Liquid
	Surface Requirements	Dry
		Clean
		Free of grease
	Surface Cleaning	Cyberbond 9999 Cleaner Spray
		Cyberbond 9999 Liquid Cleaner
	Suitable Primer	Cyberbond 9056
		Cyberbond Conditioner Pen
	Activator	Cyberbond 9090
		Cyberbond 9096
	D-Bonder	Cyberbond 9060
		Cyberbond 9065
		Cyberbond 9066
Certifications	Certifications and Declarations of	ISO 10993-5: Tests for in vitro cytotoxicity
	Conformity	ISO 10993-10: Tests for skin sensitization
		ISO 10993-11: Tests for systemic toxicity



Additional Information

Technical User Information

Cyanoacrylates are fast setting, one component and solvent free adhesives. Polymerization is initiated by present humidity. Best results are given between 40 to 70 % relative humidity and 20 to 24 °C ambient temperature.

Cyberbond standard grades are as follows:

- **Powerdrop**[®] series (stabilised ethyl ester): For hobby and DIY applications.
- Elastomer and plastic series (ethyl ester): Fast setting industrial cyanoacrylates.
- **Neomer Series** (surface insensitive ethyl ester): Cyanoacrylates for wood, leather etc.
- **xtraflex series** (rubber toughened ethyl ester): Partly flexible, heat and impact resistant.
- Metal series (ethyl ester): High performance on metal to rubber or metal to plastic.
- Low odor series (methoxy ester): Low odour and low blooming characteristics.
- **Medical series** (butyl- and octyl ester): Skin bonding in medical industrie.
- Frame Fast[®] series: For fast bonding of screens (plastics, stainless steel) on frames (aluminium, stainless steel, wood).

Storage

Cyberbond 2011 should be used within the shelf life specified on the packaging. The storage stability applies to material stored under appropriate conditions only (original unopened containers, recommended storage temperature). This Product should be stored unopened in a cool, dry place out of direct sunlight. Refer to the Technical Data section of this document for optimum storage temperatures.

Safety

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Processing

Surfaces should be clean and free from grease. Dispense adhesive to one surface only. Apply only enough to leave a thin film layer after compression. Press parts together and hold firmly until adhesive has fixtured. Maximum strength is attained typically in 24 hours. Product should be allowed to develop full strength before subjecting to any service loads.

Disposal

Please refer to the Safety Data Sheet (SDS) for disposal instructions.

Additional Programme

To support certain applications Cyberbond offers a range of additional products. Refer to the to the product properties section of this document for suitable Activators and Cleaners.

LINOP Equipment

Cyberbond offers by means of the LINOP Equipment range suitable dosing and LED based curing devices. We also refer to suitable dosing tips which help an economical use of the adhesives (also if used manually).

Tel: +49 5031 9566-0

FAX: +49 5031 9566-26

Werner-von-Siemens-Str. 2

31515 Wunstorf - Germany

H.B. Fuller	Cyberbond CB	
Cyberbond Europe GmbH		

TDS Cyberbond 2011	V01.003.eng.003

www.cyberbond.de

info@cyberbond.de

IMPORTANT: Information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.