

# Technical data sheet



Product: 5480, 5481

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: EINSEITIG

Download: 19.03.2026

## 5480/5481 PTFE SKIVED FILM TAPE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# PTFE Skived Film Tape

5480 • 5481

## Technical Data

October, 2016

**Product Description** 3M™ PTFE Skived Film Tape 5480 and 5481 tapes offer an extremely low coefficient of friction which, in combination with a pressure sensitive silicone adhesive, creates a smooth, non-stick surface over a variety of substrates to assist in the movement of web materials in many types of roll-wrap applications

Product Construction	Backing	Adhesive	Color	Standard Roll Length
	Skived PTFE (polytetrafluoroethylene)	Silicone	Gray	36 yds. (32.9 m)

## Typical Physical Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

			ASTM Test Method
<b>3M tape 5480</b>			
Adhesion to Steel:	20 oz./in. width (22 N/100 mm)		D-3330
Tensile Strength:	26 lbs./in. width (461 N/100 mm)		D-3759
Elongation at Break:	140%		D-3759
Backing Thickness:	2.0 mils (0.05 mm)		D-3652
Total Tape Thickness:	3.7 mils (0.09 mm)		D-3652
Temperature Use Range:	-65° to 500°F (-54° to 260°C)		
<b>3M tape 5481</b>			
Adhesion to Steel:	32 oz./in. width (35 N/100 mm)		D-3330
Tensile Strength:	59 lbs./in. width (1039 N/100 mm)		D-3759
Elongation at Break:	290%		D-3759
Backing Thickness:	5.0 mils (0.13 mm)		D-3652
Total Tape Thickness:	6.8 mils (0.17 mm)		D-3652
Temperature Use Range:	-65° to 500°F (-54° to 260°C)		

## Features

- Skived 3M™ PTFE Film Tapes are more conformable than typical extruded PTFE film tapes.
- Provides excellent chemical resistance except to organic solvents. **Note:** The silicone adhesive will be attacked by commercial organic solvents and so are not recommended for applications requiring organic resistance.
- Silicone adhesive provides clean removal from a variety of surfaces.
- Non-stick PTFE film provides an exceptionally slick surface for easy clean-up.

# 3M™ PTFE Skived Film Tape

5480• 5481

- 
- Application Ideas**
- Easy-release surface provided by wrapping rollers, plates, belts, etc. where build-up of sticky materials and inks can occur.
  - Shielding and protecting against chemicals.
  - Mold release for composite or metal bonding.
  - High temperature wire bundling and harnessing.
  - High strength and abrasion resistance reduce friction between surfaces, minimizing squeak and noise.
  - Wide temperature range for performance on heated machinery and equipment.

**CAUTION:** When PTFE film tape is exposed to temperatures above 600°F (316°C), small quantities of hazardous vapors may be released. **INHALATION OF THESE VAPORS MAY BE HARMFUL OR MAY CAUSE RESPIRATORY TRACT IRRITATION.** Do not heat or expose PTFE film tape to temperatures above 600°F (316°C).

---

**Storage** Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H. in the original carton.

---

**Shelf Life** To obtain best performance, use this product within 24 months from date of manufacture.

---

**Technical Information** The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

---

**Product Use** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

---

**Warranty, Limited Remedy, and Disclaimer** Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

---

**Limitation of Liability** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2000**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.

**3M**

Industrial Business  
Industrial Adhesives and Tapes Division  
3M Center, Building 220-3S-06  
800-362-3550 • 577-369-2923 (Fax)  
www.3M.com/industrial



Recycled Paper  
40% pre-consumer  
10% post-consumer

3M is a trademark of 3M Company.  
Printed in U.S.A.  
©3M 2016