

Technical data sheet



Product: GPH

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: DOPPELSEITIG

Download: 21.04.2024

3M™ VHB™ GPH-060GF/110GF/160GF

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

3M[™] VHB[™] GPH Series

Product Data Sheet

September 2022
Supersedes: September 2017

Product Description 3M[™] VHB[™] GPH Series, a general purpose, high temperature, grey conformable double coated acrylic foam tape with a high initial tack and a soft foam. Available in three different thicknesses with a 3M branded red siliconised polyethylene film liner.

- Key Features**
- Double coated acrylic foam tape
 - 100 % closed cell acrylic foam
 - High temperature performance (short term 230 °C)
 - Good balance of high temperature and peel & shear performance
 - High initial tack
 - Soft foam enables stress relaxation & an easy application
 - Good sealing properties
 - For indoor and outdoor applications

- Applications & Benefits**
- Its temperature performance enables bonding of materials in applications with high operating temperatures such as prior to processing in a powder coating line
 - Capability to bond to a variety of substrates makes it a good fit for multi material bonding - those substrates have a high or medium surface energy including many metals (e.g. stainless steel) and plastics (e.g. Polyamide, PMMA, ABS)
 - For applications in metal working, signage, appliances and specialty vehicle

Physical Properties

	GPH-060GF	GPH-110GF	GPH-160GF
Adhesive Type	Acrylic foam adhesive		
Thickness acc. to ASTM D-3652	0.60 mm	1.10 mm	1.60 mm
Foam Density	710 kg/m ³		
Release Liner	3M branded red siliconised polyethylene film		
Tape Colour	Grey		

Performance Characteristics

Type	GPH-060GF	GPH-110GF	GPH-160GF
90 ° Peel adhesion to Stainless Steel acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	25 N/cm	37 N/cm	34 N/cm
90 ° Peel adhesion to PA6 acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	33 N/cm	48 N/cm	55 N/cm
90 ° Peel adhesion to ABS acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	21 N/cm	33 N/cm	32 N/cm
90 ° Peel adhesion to PMMA acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	21 N/cm	34 N/cm	37 N/cm
Dynamic Shear acc. to ASTM D1002 on stainless steel, after 72h @ RT dwell	547 N/6.54 cm ²	476 N/6.54 cm ²	375 N/6.54 cm ²
Static Shear Strength acc. to ASTM D3654, after 72h @ RT dwell (Weight held for 10.000 minutes to stainless steel, 3.32cm ² (0.5in ²))	23 °C - 1000 g 150 °C - 500 g		
Normal Tensile (T-Block) acc. to ASTM D897 to Aluminium @ RT, after 72h @ RT dwell, 6.45 cm ² , test speed 50 mm/min	410 N/6.54 cm ²	439 N/6.54 cm ²	470 N/6.54 cm ²
Temperature Performance	Short term (minutes, hours): 230 °C Long term (days, weeks): 150 °C		

Application Temperature

Ideal application temperature range is 21 °C to 38 °C. Pressure sensitive adhesives use viscous flow to achieve substrate contact area.

Low Temperature Application:

3M™ VHB™ GPH Tape be applied at 10 °C and down to 5 °C when using 3M Adhesion Promoter AP111 or Primer 94

To obtain good performance with all 3M™ VHB™ Tapes, it is important to ensure that the surfaces are clean, dry and free of condensed moisture.

Shelf Life

24 months from date of production when stored at 16 °C – 25 °C and 40-65 % relative humidity.

Performance of tapes is not projected to change even after shelf life expires; however, 3M does suggest that 3M™ VHB™ Tapes are used prior to the shelf life date whenever possible.

**Automotive
Disclaimer**

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

3M and VHB are trademarks of the 3M Company

3M United Kingdom PLC
2M Centre, Cain Road, Bracknell
RG12 8HT
United Kingdom

3M Svenska AB
Herrjärva torg 4
170 67 Solna
Sweden

3M Eesti OÜ
Pärnu mnt. 158
11317 Tallinn
Estonia

3M Ireland Ltd
The Iveagh Building, 3rd Floor
The Park, Carrickmines 18
Ireland

3M a/s
Hannemanns Allé 53
DK-2300 Copenhagen S.
Denmark

3M Latvia SIA
K.Ulmaņa gatve 5
Rīga, LV-1004
Latvia

3M Belgium bvba/sprl
Hermeslaan 7
1831 Diegem
Belgium

3M Norge AS
Tærudgata 16
2004 Lillestrøm
Norway

3M Lietuva UAB
A.Goštauto g. 40
Vilnius LT- 03163
Lithuania

3M Nederland B.V.
Molengraaffsingel 29
2629 JD Delft
The Netherlands

Suomen 3M Oy
Keilaranta 6
02150 Espoo
Finland