

Technical data sheet



Product: 8421, 8422

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: EINSEITIG

Download: 21.12.2024

3M™ POLYESTER TAPES 8421/8422

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

3M

Polyester Tape

8421·8422

Technical Data

February 2017

Product Description	3M™ Polyester Tapes 8421 and 8422 are for the photographic industry for splicing most film for processing through the developing chemicals.			
Product Construction	Backing	Adhesive	Color	Standard Roll Length
	Polyester	Rubber	3M tape 8421 – Creamy white 3M tape 8422 – Black	72 yds. (65.8 m)
Typical Physical Properties	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.			
				ASTM Test Method
	3M Tape 8421			
	Adhesion to Steel:	42 oz./in. width (46 N/100 mm)		D-3330
	Tensile Strength:	38 lbs./in. width (665 N/100 mm)		D-3759
	Elongation at Break:	125%		D-3759
	Backing Thickness:	1.3 mils (0.03 mm)		D-3652
	Total Thickness:	2.4 mils (0.06 mm)		D-3652
	Temperature Use Range:	-60F (-50C) to 300°F (149°C)		
	3M Tape 8422			
	Adhesion to Steel:	50 oz./in. width (55 N/100 mm)		D-3330
	Tensile Strength:	43 lbs./in. width (753 N/100 mm)		D-3759
	Elongation at Break:	140%		D-3759
	Backing Thickness:	1.4 mils (0.04 mm)		D-3652
	Total Thickness:	2.5 mils (0.06 mm)		D-3652
	Temperature Use Range:	-60F (-50C) to 300°F (149°C)		
Features	<ul style="list-style-type: none"> • Frequently used in chemical baths at 150°F (66°C). • Excellent solvent and chemical resistance, especially those found in photographic processes. • Aggressive rubber adhesive grabs quickly and adheres well to a variety of films. • Hot caustics will weaken backing after prolonged immersion. • 3M tape 8422 black tape is opaque to light and can work in systems having automatic sensors. • 3M tape 8421 white backing is used to easily identify splices. 			

3M™ Polyester Tape

8421 • 8422

- Application Ideas
- Pre-splicing of most photographic film for processing (thorough testing and evaluation is suggested due to varying processing baths).
 - General wide web splicing, including butt splicing and core starting.
 - Sealing, color-coding, protecting and edging where a higher tack rubber adhesive is needed.
 - Defect marking.

Storage Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity in the original packaging material.

Shelf Life To obtain best performance, use this product within 18 months from date of manufacture.

Technical Information The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division
3M Center, Building 220-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 577-369-2923 (Fax)
www.3M.com/industrial

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2017