

# Technical data sheet



Product: 9160

Manufacturer: DOWSIL

Product group: KLEBSTOFF

Article group: 1-K SILIKON

Download: 21.05.2024

## DOWSIL™ SE 9160 ADHESIVE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



## Technical Data Sheet

### DOWSIL™ SE 9160 Adhesive

One part, bluish, reparable, hybrid (UV cure with secondary moisture cure) curable sealing product for PCB module assembly

#### Features & Benefits

- One-part UV cure with secondary moisture cure
- One part
- Bluish
- Reparable
- No added solvents
- No mixing required
- Good through (in-depth) curing in high UV energy density
- Faster in-line processing through UV curing
- Adequate flow, fill or self-leveling after dispensing
- Very low shrinkage
- Good reliability against cold and high temperature
- Good sealing against water and contaminants
- Reparable for cost-reducing

#### Applications

- Suitable for sealing air gaps or holes against water and contaminants for small-to-medium devices such as mobile, tablet and display applications (Designed to seal air gaps or holes between display (LCD/OLED) panel and plastic cover frame for mobile)
- Reparable protection sealing materials such as gaskets, masking tapes
- General application: mobile module assembly, display module assembly

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
UV cure condition at UV LED 365, 385, 405 nm	mJ/cm <sup>2</sup>	> 4,000
Color		Bluish
Viscosity	cP	20,000
Skin Over Time at 25°C	Minutes	30
Specific Gravity (Cured)		1.04
Durometer Shore A (JIS) (After UV- and 3 day moisture cure)		38

## Description

DOWSIL™ SE 9160 Adhesive is the one-part silicone based on hybrid curing (UV cure with secondary moisture cure), which provides water- & dust-proof, reliability and process-ability for PCB system assemblies.

This product can be cured at lower UV energy density (UV V: > 4,000 mJ/cm<sup>2</sup>) and full curing is achievable by room temperature moisture curing to cure shadow(or in-depth) areas of PCB system assemblies, which aren't exposed to UV light. Higher through(in-depth) curing is also achievable by higher UV energy (> 10,000 mJ/cm<sup>2</sup>) and can be adjusted, depending on the structure of each device.

The product provides a controlled flow and reparability which satisfies optimized dispensing processes and cost-saving for PCB system assembly. Faster UV curing also improves a productivity at manufacturing site since the product and components can be handled in short time right after UV curing.

Also, low cure shrinkage provides stable sealing and its elasticity provides vibration & impact resistance in assembly application.

For moisture curing part, it's generally cured at room temperature and in an environment of 30 to 80 percent relative humidity eliminating the need for curing ovens and the associated costs of energy and capital. Greater than 90 percent of full physical properties should be attained within 24 to 72 hours and varies according to product.

## Repairability

In the manufacture of PCB system assemblies, salvage or rework of damaged or defective units is often required. Removal of DOWSIL SE 9160 Adhesive to allow necessary repairs can be easily done itself or assisted by using Micsol series and IPA. After work has been completed, the repaired area should be cleaned with forced air or a brush, dried, and patched with additional silicone product.

## Packaging Information

This product is packaged in 50 cc UV-block syringes. The product may be available in all packages, and some additional packages and package sizes may be available through communication with customers.

## Usable Life and Storage

The product should be stored in freezing condition and in its original packaging with the cover tightly attached to avoid any contamination. Storage conditions and shelf life ("Use By" date) are indicated on the product label. Do not expose to UV light or sunlight to have stable shelf life. Material may polymerize upon prolonged exposure to ambient light.

## Useful Temperature Ranges

For most uses, silicone adhesives should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [consumer.dow.com](http://consumer.dow.com) or consult your local Dow representative.

## How Can We Help You Today?

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge, and processing experience to work for you.

For more information about our materials and capabilities, visit [www.consumer.dow.com](http://www.consumer.dow.com).

To discuss how we could work together to meet your specific needs, go to [consumer.dow.com](http://consumer.dow.com) for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

[consumer.dow.com](http://consumer.dow.com)

### LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

