

# Technical data sheet



Product: 4298

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: PRIMER

Article group: PRIMER

Download: 29.04.2024

## 3M™ ADHESION PROMOTER 4298UV

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Automotive Technical Datasheet

## 3M™ Adhesion Promoter

### 4298UV

#### Description

3M™ Adhesion Promoter 4298UV is intended to be used on low surface energy materials which would include PP and PP/EPDM blends (TPO). A fluorescent dye has been added so that the adhesion promoter coverage can be verified. Since formulation and surface energies vary for these substrate materials, each application should be verified through testing. 4298UV is specifically formulated to be used with 3M Acrylic Foam Tapes for Automotive applications.

#### General Properties

3M™ Adhesion Promoter 4298UV is found to be suitable for many substrates like TPU, EPDM, PE, PET, ABS or EVA. It is not suitable in combination with PVC.

#### Components

Cyclohexane, xylene, ethyl alcohol, ethylbenzene, ethyl acetate, acrylic polymer, chlorinated polyolefins, isopropyl alcohol. Contains less than 0.5% of the following:

bisphenol a-epichlorohydrin copolymer, methyl alcohol, chlorobenzene

Properties	
Colour	straw
Density	0.82 g/cm <sup>3</sup>
Viscosity	< 25 cp

#### Typical Adhesion Values

(in combination with Acrylic Foam Tapes GT6008 and 5580)

Test	Tape	Result
90°Peel Adhesion on PP EPDM 20 Minutes RT  <i>Test Speed = 300 mm/min</i>	GT6008 NLS	30 N/cm (Cohesion Failure)
	5580 NLS	38 N/cm (Pop Off PP EPDM)
90°Peel Adhesion on PP EPDM 3 Days RT  <i>Test Speed = 300 mm/min</i>	GT6008 NLS	33 N/cm (Cohesion Failure)
	5580 NLS	41 N/cm (Cohesion Failure)
90°Peel Adhesion on PP EPDM 3 days 90°C + 1 h RT <i>Test Speed = 300 mm/min</i>	GT6008 NLS	23 N/cm (Cohesion Failure)
	5580 NLS	24 N/cm (Pop Off PP EPDM)
T-Block Test on PP EPDM Stored for 240 h in 80°C*, tested in 80°C Area 25,4mm x 12,7 mm <i>Test Speed = 50 mm/min</i>	GT6008 NLS	46 N/cm <sup>2</sup> (Cohesion Failure)

\* On other substrates containing mineral oils or plasticizer the temperature performance can be decreased.



# Handling instructions 3M™ Adhesion Promoter 4298UV

## Surface Preparation

The surface must be clean which means dry, free of dust, oil, mould release agent and other impurities.

If necessary, we recommend cleaning the surface with material compatible solvents and/or to abrade slightly with abrasive paper (for extreme cases).

## Clean up

Contaminations of 4298UV can be cleaned up with MEK or Acetone.

## Application

Before using the primer, it must be shaken well and applied uniformly on the surface. Good results will be achieved with a wet coating thickness up to 50 µm. The drying time is dependent on the temperature, humidity and circulation of air as well as on the porosity of the surfaces. When the solvents are completely evaporated the coating is dry (after 30-90 seconds), bonding can be carried out. The bonding should occur within 1 hour after applying the adhesion promoter.

The recommended processing temperature for adhesion promoter and material is between 15°C and 25°C.

## Shelf Life

One year from date of receipt by customer when stored in the original container at + 4°C to + 38°C.

Storage at lower temperatures for short periods will not affect product performance if the adhesion promoter is warmed up to room temperature before application.

## Safety Instructions

See material safety data sheet

IMDS link: <http://www.mdssystem.de>

## Important notice to purchaser

All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy or completeness there of is not guaranteed. Please ensure before using our product that it is suitable for your intended use. All questions of liability relating to this product are governed by the Terms of Sale subject, where applicable, to the prevailing law.

