

# Technical data sheet



Product: 49

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: DISPERSION

Download: 03.01.2025

## 3M™ FASTBOND™ INSULATION ADHESIVE 49

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



## Technical Data Sheet

3M™ Fastbond™ Insulation Adhesive 49



[Product Details](#)



[Regulatory Info/SDS](#)

### **Product Description**

3M™ Fastbond™ Insulation Adhesive 49 is a water-based, high solids, fast tacking, pressure sensitive adhesive for bonding lightweight materials like fiberglass insulation, felt, shoddy, paper and other materials to metal and many other surfaces.

### **Product Features**

- Water-based, non-flammable in the wet state.
- Spray, brush, or roll apply.
- High coverage.
- Instant tack on fiberglass insulation.
- Permanently pressure sensitive with aggressive tack.
- Recognized by Underwriters Laboratories, Inc., Component Recognition Category MAGW2 (Adhesives, Insulation), File Number MH 6288.
- Certified to GREENGUARD® Product Emission Standard For Children and Schools(SM) for low emitting interior building materials:
  - Addresses or Contributes to LEED® EQ Credit 4.1: Low Emitting Materials: Adhesive and Sealants
  - Addresses or Contributes to LEED® EQ Credit 4.5: Low Emitting Materials: Furniture and Furnishings
  - Addresses or Contributes to LEED® EQ Credit 4.6: Low Emitting Materials: Ceiling and Wall Systems



### **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Uncured Physical Properties

Attribute Name	Value
Net Weight	8.25 lb/gal
Base	Acrylate

## Typical Physical Properties

Attribute Name	Temperature	Value
Color		Milky White (wet), Clear (dry)
Solids Content by Weight		53 to 57 %
pH		4.1 to 4.5
Coverage		824 ft <sup>2</sup> /gal <sup>1</sup>
Flammability (Dry)		Combustible
Flammability (Wet)		Non-Flammable
Viscosity	22 °C (72 °F)	450 to 650 cP <sup>2</sup>

<sup>1</sup> 2.5 gms. ft<sup>2</sup> [dry wt.]; For most HVAC applications. Coverage for other applications may be lower.

<sup>2</sup> Brookfield Viscometer RVF #3 Sp. @ 20 rpm

## Typical Performance Characteristics

### 180° Peel Adhesion

Temperature: 22 °C (72 °F)

Dwell Time: 48 h

Substrate	Value
ABS	75 oz/in <sup>1</sup>
Acrylic (PMMA)	62 oz/in <sup>1</sup>
Clad Aluminum	45 oz/in <sup>1</sup>
EPDM Rubber	16 oz/in <sup>1</sup>
High Density Polyethylene (HDPE)	8 oz/in <sup>1</sup>
Neoprene Rubber	21 oz/in <sup>1</sup>
Polycarbonate (PC)	83 oz/in <sup>1</sup>
Polypropylene (PP)	35 oz/in <sup>1</sup>
Polystyrene (High Impact)	90 oz/in <sup>1</sup>
Polyvinyl chloride (PVC)	72 oz/in <sup>1</sup>
Stainless Steel	51 oz/in <sup>1</sup>

<sup>1</sup> Adhesive was tested in 180° (angle) peel, overlap shear, and dead load strength by first applying a 6 mil (wet thickness) coating of adhesive to a primed polyester film. After drying, bonds were made to various substrates.

### Overlap Shear Strength

Temperature: 22 °C (72 °F)

Dwell Time: 48 h

Substrate	Value
Glass	53 lb/in <sup>2</sup> <sup>1</sup>
Cold Rolled Steel	57 lb/in <sup>2</sup> <sup>1</sup>
2024 T3 Aluminum	51 lb/in <sup>2</sup> <sup>1</sup>
Clad Aluminum	52 lb/in <sup>2</sup> <sup>1</sup>
Stainless Steel	52 lb/in <sup>2</sup> <sup>1</sup>
High Density Polyethylene (HDPE)	34 lb/in <sup>2</sup> <sup>1</sup>
Polypropylene (PP)	39 lb/in <sup>2</sup> <sup>1</sup>

Substrate	Value
High Impact Polystyrene	53 lb/in <sup>2</sup> <sup>1</sup>
Polyvinyl chloride (PVC)	56 lb/in <sup>2</sup> <sup>1</sup>
ABS	50 lb/in <sup>2</sup> <sup>1</sup>
Polycarbonate (PC)	57 lb/in <sup>2</sup>
Acrylic (PMMA)	52 lb/in <sup>2</sup> <sup>1</sup>
Neoprene Rubber	12 lb/in <sup>2</sup> <sup>1</sup>
EPDM Rubber	14 lb/in <sup>2</sup> <sup>1</sup>

<sup>1</sup> Adhesive was tested in 180° (angle) peel, overlap shear, and dead load strength by first applying a 6 mil (wet thickness) coating of adhesive to a primed polyester film. After drying, bonds were made to various substrates.

Test Method: ASTM E84

Attribute Name	Value
Flame Spread	1.8 <sup>1</sup>
Smoke Developed Index	4 <sup>2</sup>

<sup>1</sup> Tunnel test results; Test at a roverage rate of 800 sqft/gal; UL Requirement: Less than 25

<sup>2</sup> Tunnel test results; Test at a roverage rate of 800 sqft/gal; UL Requirement: Less than 50

## **Typical Environmental Performance**

Attribute Name	Value
Accelerated Aging	Adhesive was spray applied to pieces of 1.5 lb. per cubic foot density fiberglass insulation at the recommended coverage rate. The fiberglass was then bonded to galvanized steel panels and allowed to air dry for 24 hours. After drying, the bonded panels were aged in a 320°F (160°C) oven for 60 days. Bond strength sufficient to tear fiberglass was observed after aging. <sup>1</sup>

<sup>1</sup> Adhesive was spray applied to pieces of 1.5 lb. per cubic foot density fiberglass insulation at the recommended coverage rate. The fiberglass was then bonded to galvanized steel panels and allowed to air dry for 24 hours. After drying, the bonded panels were aged in a 320°F (160°C) oven for 60 days. Bond strength sufficient to tear fiberglass was observed after aging.

## **Typical Environmental Characteristics**

### **Wet Strength**

Adhesive was spray applied on 6 in x 12 in x 1.0 in pieces of 1.5 lb. per cubic foot density fiberglass insulation at the recommended coverage level. After 1 minute of drying at room temperature, the fiberglass was bonded (using hand pressure) to 6 in x 12 in galvanized steel panels pre-bent to form a 90° angle. The wet strength of the adhesive was sufficient to hold the fiberglass in place.

### **Humidity Resistance**

As above, 1.5 lb. per cubic foot density fiberglass was bonded to galvanized steel and aged for 60 days at 140°F (60°C) and 95-100 percent relative humidity. Bond strength sufficient to tear fiberglass was observed after aging.

### **Temperature Resistance**

The bonded panels above were allowed to air dry for 24 hours and then they were placed in 127°F (53°C) oven for 15 minutes. The temperature was then raised 18°F (8°C) every 10 minutes until 325°F (162°C) was achieved. No failure of the fiberglass to the substrate was observed within this temperature range.

## **Handling/Application Information**

### **Directions for Use**

Setting Up the 3M™ Fastbond™ Insulation Adhesive 49 Container for Dispensing: Suggested equipment for dispensing is outlined in the section under Application Equipment. If using open head drums or totes it is suggested that one check for dried skins on the surface and remove them prior to using the product. For containers using a flexible poly bag skinning should not occur. For hook up considerations the outlet for the various containers are:

Schutz tote - 2" male cam lock  
 EZ-Bulk tote - 1.5" FNPT  
 Drum - 2" FNPT or 3/4" FNPT  
 Hedwin Box uses a 38 MM 400 finish screw on cap

**Applications:** Adhesive may be applied by spray, brush or paint roller. Apply a uniform, generous coat of adhesive to one of the surfaces to be bonded (porous surface preferred.) Very porous material may require more than one coat. (Allow adhesive to dry completely between coats).

**Coverage:** Coverage is dependent upon porosity of the substrate and the method by which the adhesive is applied. To bond fiberglass insulation, apply the adhesive to the insulation in a uniform pattern at a coverage rate between 1.0 -2.0 dry gms./sqft (2000 sqft to 1000 sqft/gallon). (Additional adhesive may be required for heavier materials).

**Drying:** Allow adhesive to dry until the surface becomes tacky. The insulation may then be bonded using hand pressure. Bonded parts may be handled immediately.

**Cleanup:** Wet adhesive may be removed using soapy water. For dry adhesive removal, use 3M™ Scotch-Weld™ Solvent No. 3 (Methyl Ethyl Ketone), or 3M™ Citrus Base Cleaner, or isopropyl alcohol.\*

\*Note: When using solvents, extinguish all ignition sources and follow manufacturer’s precautions and directions for use.

**Surface Preparation**

Surfaces must be clean, dry and dust free. Remove all dirt, dust, oil, grease, wax, loose paint, etc. to ensure proper adhesion.

**Application Equipment**

**Note:** Appropriate application equipment can enhance adhesive performance. We suggest the following application equipment for the user’s evaluation in light of the user’s particular purpose and method of application.  
 Air Atomizing Spray Equipment

Spray Guns

Type	Example	Air Cap	Fluid Tip	Atomizing Air Pressure <sup>2</sup>
Pressure fed, hand held spray	Binks Model 2001 SS	66S	63A SS (.040")	25 psi
	Binks Model 95	66S	63A SS (.040")	25 psi
Gravity fed, hand held	Binks 2001 SS	Tornado Tip <sup>1</sup>	0.070"-0.096" <sup>1</sup>	40 psi
	Binks Model 95 SS	Tornado Tip <sup>1</sup>	0.070"-0.096" <sup>1</sup>	40 psi

**Note:** Gravity fed systems are preferred to minimize fluid shear.

<sup>1</sup>Air cap and fluid tip combination available from U.S. Legends, Inc.

<sup>2</sup>Starting air pressure on regulator. Adjust up and down based on application requirements.

Pressure Pots

Stainless steel pressure pots recommended. Non-stainless may be used with plastic liners if dip tube and fittings are changed to plastic or stainless steel.

Pumping Equipment

Due to the shear sensitivity of this product pumping is not recommended. If pumping is under consideration please consult with your local 3M sales representative.

Filter (Between Gun and Fluid Source)

The use of a 40-mesh stainless steel strainer is suggested to filter any impurities or dried adhesive that may have entered the system.

Hoses

Hoses used with pressure pots should be nylon or polyester lined. For gravity feed systems a clear PVC hose with a 0.5" inside diameter is adequate. Avoid using fluid hoses that have previously been used with solvent.

Brushes and Rollers

Typical brushes and rollers designed for use with latex paints may be used.

## **Industry Specifications**

- Recognized by Underwriters Laboratories, Inc., Component Recognition Category MAGW2 (Adhesives, Insulation), File Number MH 6288.
- Certified to GREENGUARD® Product Emission Standard For Children and Schools(SM) for low emitting interior building materials:
  - Addresses or Contributes to LEED® EQ Credit 4.1: Low Emitting Materials: Adhesive and Sealants
  - Addresses or Contributes to LEED® EQ Credit 4.5: Low Emitting Materials: Furniture and Furnishings
  - Addresses or Contributes to LEED® EQ Credit 4.6: Low Emitting Materials: Ceiling and Wall Systems

## **Storage and Shelf Life**

Protect from freezing! Best storage temperature is 60-80°F (15-27°C). Higher temperatures reduce normal storage life. Lower temperatures can cause increased viscosity of a temporary nature. This water-based adhesive will become unusable with prolonged storage below 40°F (4°C). Rotate stock on a "first in, first out" basis. When stored at recommended temperature in the original, unopened container, this product has a shelf life of 18 months from date of manufacture.

## **Precautionary Information**

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

## **Automotive Disclaimer**

**Select Automotive Applications:** This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M  
Industrial Adhesives and Tapes Division  
3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550

3M, Fastbond and Scotch-Weld are trademarks of 3M.  
©3M 2022 (5/22)