

# Technical data sheet



Product: 760

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: DICHTMASSE

Download: 13.05.2026

## 3M™ HYBRID ADHESIVE SEALANT 760

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Hybrid Adhesive Sealant 760

## Product Data Sheet

Date: September 2022  
Supersedes: February 2013

### Product Description

3M™ Hybrid Adhesive Sealant 760 is a one component sealant without isocyanates which forms permanent elastic bonds. It cures rapidly under the effect of atmospheric humidity to form a flexible and resistant joint with very good adhesion on most materials.

Is suitable for industrial and refrigerated trailers, truck bodies, shipbuilding, air conditioning and ventilation units, sandwich panels and many other industrial applications.

Can also be used for bonding and caulking different materials used in the building industry: concrete, wood, aluminium, most lacquered metals, polyester, glass, concrete, brick, stone, ceramic, etc.)

However, for difficult materials (especially lacquered or non-ferrous metals), it is necessary to make tests. Please contact your local 3M representative in that case.

### Key Features

Features	Advantages
One component/moisture curing	<ul style="list-style-type: none"><li>No Mixing</li><li>Simplifies production</li></ul>
Neutral product	<ul style="list-style-type: none"><li>no isocyanates</li></ul>
Seals dissimilar materials	<ul style="list-style-type: none"><li>Gives design flexibility</li></ul>
Adheres to a wide variety of materials	<ul style="list-style-type: none"><li>Multiple uses and design flexibility</li></ul>
Permanently elastic	<ul style="list-style-type: none"><li>Provides long lasting bonds</li></ul>
Fast curing	<ul style="list-style-type: none"><li>Speeds production</li></ul>
Paint-able	<ul style="list-style-type: none"><li>yes</li></ul>

### Technical Data

	3M Hybrid Sealant 760
Skin formation time (min) (ISO 291, 23°C, 50% RH)	20min ± 10min
Cure time, mm/24h (ISO 291, 23°C, 50% RH)	3 mm / 24 h
Shore A Hardness (ISO 868-3 seconds)	Approx. 55
Density (g/ml) (DIN EN ISO 2811-2)	White and grey : 1,62 ± 0,05 Black : 1,57 ± 0,05
Elongation at Break (ISO 37)	>300%
Modulus at 100% (ISO 37)	> 1 MPa
Modulus at break (ISO 37)	> 1.8 MPa
Tensile Strength at 100% elongation (ISO 8339)	0.62 MPa

Tensile shear at break (ISO 8339)	1.15 MPa
Sagging (mm) (ISO 7390)	None
Volume loss (%) (ISO 10563)	4,4% (white) 7,1 % (black)
Colours	Grey, white, black
Application temperature	5°C to 35°C
Consistency	Thick paste
UV resistance	Excellent
Compatibility with paints	Water based : yes Solvent based : testing required

### UV Properties

The product has good resistance to UV aging and will retain strength and flexibility over long-term exposure to UV light. The white product may show some yellowing with long-term exposure to UV light.

### Direction for use

#### Surface Preparation:

Surfaces to be sealed or bonded must be clean, dry and be free from grease, mould release, oil, water/condensation and other contaminants that may affect the adhesion of the sealant. Abrading with 180 to 220 grit abrasive followed by a solvent wipe will improve the bond strength. Suitable solvents include 3M™ Citrus Based Adhesive Remover, 3M™ Scotch-Weld™ Solvent No. 2 or methyl ethyl ketone (MEK).

**When using solvents, use in a well ventilated area. Extinguish all sources of ignition in the work area and observe product directions for use and precautionary measures. Refer to product label and MSDS for further precautions. Always pre-test solvent to ensure it is compatible with substrates.**

#### Application:

Puncture seal in nozzle and knock out the thin seal at cartridge bottom before placing in a pneumatic caulking gun. (For flex packs cut off the small crimp at the end and then place in caulking gun barrel with the open end up). Assemble tip and retaining ring on gun, cut tip to desired size. Product should be used within 24 hours after seal is punctured and should be pressed firmly into the joint to ensure adequate contact of the sealant with the substrate.

Apply product when temperatures are between 5° C and 35° C. In cold weather, store the product at about 20 °C before use. Do not apply on frozen surfaces or wet surfaces.

Do not apply over silicones or in the presence of curing silicones.

Avoid contact with alcohol and solvents during curing.

Sealant can be tooled immediately after applying to give desired appearance, such as using a putty knife to smooth the joint with soapy water.

Avoid any contact with non-cured hybrid sealant during curing.

#### Cleanup:

While sealant is still soft cleaning can be done with the same solvents used for surface preparation. If sealant is already cured, removal is done mechanically with razor knife, piano wire, sanding or 3M™ Scotch-Brite™ Moulding Adhesive and Stripe Removal Disc. This disc is available from 3M Automotive Aftermarket Division.

---

<b>Application Equipment Suggestions</b>	<b>Cartridge, Flex Pack, Bulk dispensing</b> Please contact your local 3M representative
--	---

---

<b>Shelf Life</b>	9 months in the original, hermetically sealed packaging between 5°C and 25°
-------------------	---

---

<b>Precautionary Information</b>	Refer to product label and Material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office. <a href="http://www.3M.com">www.3M.com</a>
----------------------------------	--

---

<b>For Additional Information</b>	To request additional product information or to arrange for sales assistance, call 0870 6080050 Address correspondence to: 3M United Kingdom PLC, 3M House, 28 Great Jackson Street, Manchester, M15 4PA
-----------------------------------	--

---

<b>Automotive Disclaimer</b>	<p>Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.</p> <p>NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.</p>
------------------------------	---

**Important Notice**

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of the 3M Company.

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA	Product Information :  Tel 0870 60 800 50 Fax 0870 60 700 99	3M Ireland Limited The Iveagh Building The Park, Carrickmines Dublin 18, Ireland	Customer Service :  Tel (01) 280 3555 Fax (01) 280 3509
--	---	--	--