

# Technical data sheet



Product: PR 100

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: CYANACRYLAT

Download: 24.06.2026

## 3M™ SCOTCH-WELD™ CYANOACRYLATE PR100

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Scotch-Weld™ Cyanoacrylate Adhesive PR100

## Product Data Sheet

Updated :February 2010  
Supersedes:February 2007

**Product Description** Scotch-Weld PR100 is a medium viscosity (100 cPs) Ethyl Cyanoacrylate based adhesive. PR100 is formulated for high speed, high strength bonding of plastics and rubbers but is also suitable for bonding a very wide range of materials.

**Key Features** PR100 is specially formulated for high strength, general purpose bonding of most plastics and rubbers. Recommended for use on assemblies with close fitting parts and relatively smooth, even surfaces.  
**Scotch-Weld PR grade cyanoacrylates are certified to USP Class VI**

<b>Physical Properties</b>	<b>Base</b>	Ethyl
	<b>Soluble In</b>	Acetone, MEK
	<b>Viscosity (cps)</b>	Range 80-120 Typical Value 100
	<b>Specific Gravity</b>	1.06
	<b>Colour</b>	Clear

<b>Performance Characteristics</b>	<b>Maximum Gap Fill</b> (best results are obtained with very thin bond lines)	0.15mm
	<b>Fixture Time</b>	10-30secs
	<b>Tensile Strength</b> (ISO 6922)	20 N/mm <sup>2</sup>
	<b>Full Cure</b>	24hrs
	<b>Speed of Cure</b>	The speed of cure of cyanoacrylates varies according to the substrate to be bonded. Acidic surfaces such as paper and leather will have longer cure times than most plastics and rubbers.
	<b>Moisture Resistance</b>	Low resistance to high levels of moisture and humidity over time.
	<b>Service Temperature Range</b>	-50 to +80°C

---

<b>Additional Product Information</b>	Scotch-Weld Activators AC11 and AC12 may be used in conjunction with Scotch-Weld cyanoacrylates where cure speed needs to be accelerated. Cure speeds of less than 2 seconds can be obtained with most Scotch-Weld cyanoacrylates. The use of an activator can reduce the final bond strength by up to 30%.
<b>Application Techniques</b>	Bond speed is very fast so ensure that parts are properly aligned before bonding. Scotch-Weld Activators may be required if there are gaps or porous surfaces. Some plastics may require application of Scotch-Weld AC77 Primer. Ensure parts are clean, dry and free from oil and grease. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved. As a general rule, as little cyanoacrylate as possible should be used – over application will result in slow cure speed and lower bond strength.
<b>Storage Conditions</b>	Keep the adhesive in a cool, dry place away from direct sunlight. Under such conditions shelf life at room temperature will be 12 months.  Refrigeration to 5°C gives optimum storage stability.
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C
<b>Precautionary Information</b>	Refer to product label and material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office. <a href="http://www.3M.com">www.3M.com</a>
<b>For Additional Information</b>	To request additional information or to arrange for sales assistance, please see below for contact details.
<b>Important Notice</b>	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---



**3M Svenska AB  
Industri**

Bollstanäsvägen 3  
191 89 Sollentuna  
Tel: 08-92 21 00  
Fax: 08-92 22 88  
E-post:  
[kundservice@mmm.com](mailto:kundservice@mmm.com)  
[www.3M.se/lim](http://www.3M.se/lim)

**3M a/s  
Industri**

Hannemanns Allé 53  
2300 København S  
Tlf.: 43 48 01 00  
Fax.: 43 20 15 65  
E-mail:  
[dkindustri@mmm.com](mailto:dkindustri@mmm.com)  
[www.3Mindustri.dk](http://www.3Mindustri.dk)

**3M Norge AS  
Avd. Industri**

Hvamveien 6  
2013 Skjetten  
Tel: 0 63 84  
Fax: 63 84 17 88  
E-post:  
[Kundeservice@mmm.com](mailto:Kundeservice@mmm.com)  
[www.3M.no/lim](http://www.3M.no/lim)

**Suomen 3M Oy  
Teollisuustuotteet**

PL 600  
Keilaranta 6  
02151 Espoo  
Puh: 09-525 21  
Fax: 09-525 2279  
<http://www.3M.fi/teollisuus>