

# Technical data sheet



Product: 3731

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: SCHMELZKLEBSTOFF

Download: 12.03.2026

## 3M™ POLYOLEFIN BONDING ADHESIVE 3731

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Technical Data Sheet

## 3M™ Polyolefin Bonding Adhesive 3731



[Product Details](#)



[Regulatory Info/SDS](#)

### **Product Description**

3M™ Polyolefin Bonding Adhesive 3731 is a 100% solids, high heat resistant adhesive that bonds to a variety of substrates including polyethylene, polypropylene and many other plastics.

### **Product Features**

- Solvent free, 100% solids
- High temperature resistance
- Bonds well to polyolefin based plastics
- Light tan color
- Fast setting

### **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### **Typical Physical Properties**

Attribute Name	Test Method	Temperature	Value
Color			Light Tan
Flash Point			273 °C (525 °F) <sup>1</sup>
Ball & Ring	ASTM E-28-607		157 °C (315 °F)
Specific Gravity			0.92
Viscosity		191 °C (375 °F)	12,000 cP <sup>2</sup>

<sup>1</sup> C.O.C.

<sup>2</sup> Brookfield Thermocel Viscometer in Centipoise using a #27 Spindle @ 10 RPM.

### **Typical Performance Characteristics**

#### **180° Peel Adhesion**

Temperature: 22 °C (72 °F)

Substrate	Value
ABS	368 oz/in <sup>1</sup>
Cold Rolled Steel	240 oz/in <sup>1</sup>
High Density Polyethylene (HDPE)	368 oz/in <sup>1</sup>
Nylon	304 oz/in <sup>1</sup>
Polycarbonate (PC)	352 oz/in <sup>1</sup>
Polypropylene (PP)	352 oz/in <sup>1</sup>
Polystyrene (High Impact)	240 oz/in <sup>1</sup>
Polyvinyl chloride (PVC)	288 oz/in <sup>1</sup>

<sup>1</sup> Peel bonds of cotton duck were tested at a peel angle of 180° @ 2in/min separation rate @RT. The value listed is the average force required to peel the canvas from the substrates in pounds per inch of bond width (PIW).

#### **Overlap Shear Strength**

Temperature: 22 °C (72 °F)

Substrate	Value
High Density Polyethylene (HDPE)	420 lb/in <sup>2</sup>
ABS	450 lb/in <sup>2</sup>
P.V.C. (Rigid)	430 lb/in <sup>2</sup>
Polystyrene (High Impact)	257 lb/in <sup>2</sup>
Polycarbonate (PC)	430 lb/in <sup>2</sup>
Nylon	475 lb/in <sup>2</sup>
Douglas Fir	490 lb/in <sup>2</sup>
Cold Rolled Steel	390 lb/in <sup>2</sup>

### Temperature Resistance

Temperature	Value
129 °C (265 °F)	0.14 kg/cm <sup>2</sup> (2 lb/in <sup>2</sup> )
135 °C (275 °F)	0.07 kg/cm <sup>2</sup> (1 lb/in <sup>2</sup> )
152 °C (305 °F)	0.02 kg/cm <sup>2</sup> (0.33 lb/in <sup>2</sup> )

### Handling/Application Information

#### Directions for Use

1. 3M™ Polyolefin Bonding Adhesive 3731 is designed for applications using a 3M™ Polygon™ EC Applicator at the 4 or 5 module setting or a 3M™ Polygun™ II Applicator.
2. Recommended equipment temperature for bulk dispensing 350-375°F (177-191°C).
3. Apply to one surface. Make bond as soon as possible. Bond strength is maximized when open time is reduced.
4. After bond is made, there is immediate strength and no clamping is necessary.
5. Adhesive should be allowed to fully crystallize (possibly up to 12 hours) to obtain full performance properties.

### Storage and Shelf Life

Store product below 120°F (49°C).

When stored at the recommended conditions, this product has a shelf life of 24 months from date of manufacture.

### Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

### Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with

product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## **For Additional Information**

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit [www.3M.com/adhesives](http://www.3M.com/adhesives). Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

3M  
Industrial Adhesives and Tapes Division  
3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550

©3M 2015 (2/15)