

Technical data sheet



Product: 3779

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: SCHMELZKLEBSTOFF

Download: 26.12.2024

3M™ HOT MELT ADHESIVE 3779

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708



Technical Data Sheet

3M™ Hot Melt Adhesive 3779



[Product Details](#)



[Regulatory Info/SDS](#)

Product Description

3M™ Hot Melt Adhesives are heat applied, 100% solids adhesives. 3M™ Hot Melt 3779 is a thermoplastic adhesive to bond to wide variety of substrates such as wood, plastic, vinyl, metal and glass.

- High strength bonding with excellent environmental stability including very high heat resistance. Fast set time.

Product Features

- 100% solids, no VOCs
- Easy to use
- Long open times allow for easy use on large assemblies and large surfaces
- Adhesive sets and obtains strength in seconds
- Creates high performance bonds
- Ideal for woodworking and general industrial applications.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Test Method	Temperature	Substrate	Value
Color				Amber
Density				0.99 g/cm ³ (0.036 lb/in ³)
Open Time			OSB	25 s ¹
Flash Point	ASTM D92-72			288 °C (550 °F) ²
Delivery Time				75 s ³
Viscosity		191 °C (375 °F)		7,000 cP ⁴

¹ Open time is the max time between the application of the adhesive and joining the parts. Data based on 1/8in semicircular bead on non-metallic substrates at 75°F. Higher environmental temperatures and/or larger beads will lengthen open times.

² Cleveland Open Cup

³ Extrusion time for one 1"x3" PG cartridge.

⁴ Brookfield Thermocel Viscometer in Centipoise using a #27 Spindle @ 10 RPM.

Typical Performance Characteristics

Attribute Name	Test Method	Temperature	Substrate	Value
180° Peel Adhesion		22 °C (72 °F)	Flexible canvas bonded to Douglas Fir	288 oz/in
Overlap Shear Strength		22 °C (72 °F)	Douglas Fir	700 lb/in ²
Ball & Ring Melt Point	ASTM E28-67			163 °C (325 °F)

Attribute Name	Value
Application Temperature	177 to 196 °C (350 to 385 °F) ¹
Temperature Resistance	149 °C (300 °F) ²

¹ Recommended application temperature range. Temperature can be adjusted to regulate desired viscosity, delivery rate and pot life.

² Highest temperature that the adhesive will support a 2 psi dead load

Handling/Application Information

Directions for Use

1. Surface Preparation: Surfaces must be clean, dry and dust free. Wipe with a solvent such as isopropyl alcohol for plastic, metal and glass substrates to remove oil and dirt.*

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

2. Application: 3M™ Hot Melt Adhesives are designed for application with a 3M™ Hot Melt Applicators. Read and follow the precautions and directions for use in the user's manual before operating the applicator. 3M™ Hot Melt Adhesives are applied at 350-385°F. Adhesives yield approximately 430 linear feet per pound of adhesive when extruded as a 1/8" diameter semi-circular bead. Extruded bead sizes can be customized using 3M™ applicator tips.

3. Coverage: 3M™ Hot Melt Adhesives yield approximately 430 linear feet per pound of adhesive when extruded as a 1/8" diameter semi-circular bead.

4. Set up time: After the bond is made, 3M™ Hot Melt Adhesives immediately build strength and no clamping is necessary. Set will occur faster on cold or metallic substrates.

Storage and Shelf Life

Store product below 120°F (49°C).

When stored at the recommended conditions, this product has a shelf life of 24 months from date of manufacture.

Available Sizes - Detailed

5/8 in x8 in Q
5/8 in x2 in TC
1 in x3 in PG
1/8 in Bulk

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M
Industrial Adhesives and Tapes Division
3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550

3M is a trademark of 3M.
©3M 2016 (7/16)