

# Technical data sheet



Product: 9225

Manufacturer: HENKEL KGAA

Product group: KLEBSTOFF

Article group: 2-K KLEBSTOFF

Download: 28.04.2024

## TEROSON PU 9225 SF ME

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708

# TEROSON PU 9225 SF ME

November 2013

## Super fast curing material, Micro Emission

### PRODUCT DESCRIPTION

<b>Technology</b>	Polyurethane, Micro Emission
<b>Product Type</b>	For the repair of plastic parts
<b>Additional Information</b>	2-Component

TEROSON PU 9225 SF ME is a polyurethane based two-component adhesive which cures at room temperature. For accelerated curing it is recommended to increase the temperature up to 60 to 70 °C. The product is supplied in a convenient twin cartridge and is rapid-curing. TEROSON PU 9225 SF ME can be painted with normal commercial car repair refinishing paints. When applying TEROSON PU 9225 SF ME to plastics the use of an approved Henkel primer is absolutely necessary. Detailed information see directions of use.

### APPLICATION AREAS

TEROSON PU 9225 SF ME is used for repair of bumpers, trim and body parts made of plastic e.g. PP / EPDM, SMC, PC, PA, ABS, and PUR.

### TECHNICAL DATA (Typical Test Results)

#### COMPONENT A

Colour grey  
Density approx. 1.6 g/cm<sup>3</sup>

#### COMPONENT B

Colour white  
Density approx. 1.3 g/cm<sup>3</sup>

#### Mixing ratio A : B

By volume 1 : 1

#### MIXTURE (Component A + B)

Colour grey  
Potlife (25 g, 23 °C) approx. 2 min(s)  
Tack-free time (23 °C, 50 % rh) approx. 20 min(s).  
Curing time at 23 °C approx. 1.5 hr(s).  
Layer thickness 3 mm  
Shore A hardness approx. 95  
Grindability good  
Shear strength  
After 2 d (23 °C, 50 % rh) approx. 8 MPa  
Layer thickness 0.3 mm  
Cross head speed 10 mm/min.  
Paintability good

### PRELIMINARY STATEMENT

Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

### DIRECTIONS OF USE Pretreatment

The parts to be bonded must be free from oil, grease, moisture, dirt and release agents. Pre-cleaning with a high pressure injection cleaner is recommended. After drying the parts should be cleaned with Teroson FL+. Damaged plastic parts have to be sanded on the face side with a narrow belt sander (grit P 80 to 120) to grind a V-groove (1 to 2 cm). Finally the sanded parts should be cleaned with Teroson FL+. When applying TEROSON PU 9225 SF ME to plastics the use of primer Teroson 150 in a thin layer is absolutely necessary. Evaporation time is approx. 10 minutes.

### Application

Insert the cartridge into a suitable application gun. Apply pressure to the cartridge(s) to ensure a simultaneous and homogeneous flow of both components. Thereafter, attach the static mixer and cut the tip to provide for the desired bead size. Discard the first 2 cm of extruded adhesive bead. TEROSON PU 9225 SF ME is applied directly to the substrates. Any excess material should be removed immediately after application. If material is left in the cartridge leave the static mixer attached. For further use of the product, simply remove the mixer and install a new one. In case of plastic repair the use of woven fibreglass mat is recommended for reinforcing.

### Reinforcing

In the case of simple cracks TEROSON PU 9225 SF ME can be applied in one step to both, the face side and the rear side. For more difficult damages, the adhesive should be applied to both sides separately. Start with two continuous beads on the rear side and place them to both sides of the damaged area (bond with minimum 100 mm). For large damages e.g. holes, it is recommended to reinforce the complete damaged area with woven fibre glass mat by incorporating the mat in the beads. Reinforce initial crack areas with woven glass fibre mat in the same way. Then apply TEROSON PU 9225 SF ME on top of the reinforced matting and smooth the surface. Ensure that the adhesive is pressed through the crack and the fibre glass mat to the front side to guarantee a reliable bonding. During applying TEROSON PU 9225 SF ME, keep the mixer tip within the material to avoid air inclusions. Apply an excess of TEROSON PU 9225 SF ME in the same way to the front side.



# TEROSON PU 9225 SF ME

November 2013

## Curing

Curing occurs at room temperature. For accelerated curing it is recommended to use a heat source. To get a faster grindability the parts bonded with TEROSON PU 9225 SF ME can be warmed up to 60 to 70 °C for minimum 3 to 4 minutes.

## Pretreatment for finish

After curing of the material these following steps are necessary:  
Sanding and cleaning (P150/ P240, TEROSON FL+); priming (TEROSON 150); Further treatment e.g. filling, painting has to be carried out according to paint manufacturers directions for painting plastics.

## Cleaning

Freshly applied and uncured material should be removed with a dry cloth and then cleaned off with a suitable solvent. Cured adhesive can only be removed with the use of a machine.

## STORAGE

Frost sensitive	no
Recommended storage temperature	10 to 25 °C
Shelf life	12 months

## Disclaimer

### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

## Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.





# TEROSON PU 9225 SF ME

November 2013

---

**Henkel AG & Co. KGaA**  
D-40191 Düsseldorf, Germany  
Phone: +49-211-797-0  
[www.henkel.com](http://www.henkel.com)

**Henkel Central Eastern Europe GmbH**  
A-1030 Wien, Austria  
Phone: +43-1711-040  
[www.henkel.com](http://www.henkel.com)

**Henkel & Cie AG**  
CH-4133 Pratteln, Switzerland  
Phone: +41-61-825-7000  
[www.henkel.com](http://www.henkel.com)

