

Technical data sheet



Product: 7094

Manufacturer: DOWSIL

Product group: KLEBSTOFF

Article group: 1-K SILIKON

Download: 20.05.2024

DOWSIL™ 7094 FLOWABLE SEALANT

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708



Technical Data Sheet

DOWSIL™ 7094 Flowable Sealant

One-part, flowable neutral cure silicone sealant

Features & Benefits

- One-part sealant
- Cures at room temperature when exposed to moisture in the air
- Alkoxy cure system
- Flowable and self-leveling
- Easy to apply
- Excellent unprimed adhesion to many substrates
- Stable and flexible from -50°C to +180°C
- Non-corrosive to metals
- Low odor
- Unprimed adhesion to various substrates

Composition

- Silicone sealant

Applications

- Sealing and bonding application where low viscosity and self-leveling properties in combination with non-corrosive cure is required
- Designed for applications which demand a strong but flexible bond such as when bonding materials with differing thermal expansion rates e.g., glass to metal or glass to plastic
- Low modulus formulation for high movement capability
- Sealing in gaps where an elastic grouting is required

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

CTM ¹	Property	Unit	Result
	As supplied		
	Appearance		Black or white, viscous liquid
0097B	Density	g/cm ³	1.30
0050	Viscosity	mPa·s	28,000
0098	Skin-over-time (23°C, 50% R.H.)	min	25
0095A	Tack-free-time (23°C, 50% R.H.)	min	50

1. CTM: Corporate Test Method, copies of CTM's are available on request.

Typical Properties (Cont.)

CTM	Property	Unit	Result
Mechanical properties, cured 7 days in air at 23°C and 50% R.H.			
0137A	Tensile strength	mPa	1.2
0137A	Elongation at break	%	400
0137A	Modulus @ 100%	mPa	0.36
0099	Hardness, Shore A		19

Description

DOWSIL™ 7094 Flowable Sealant is a black or white, viscous liquid, low modulus silicone sealant designed for applications where a flowable product and non-corrosive cure with durable adhesion to a variety of substrates is required. The flowable properties allow spray-applications by airless pumps.

How to Use

Substrate Preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion. Suitable solvents include isopropyl alcohol, acetone or methyl ethyl ketone. Unprimed adhesion may be obtained by on many substrates such as glass, metals (e.g. steel, aluminum) and most common engineering plastics (e.g. polyamide, polycarbonate). Adhesion may be less successful on some low energy plastics such as polyethylene, polypropylene and PTFE.

How to Apply

DOWSIL™ 7094 Flowable Sealant is ready to use. Apply a suitable amount of DOWSIL™ 7094 Flowable Sealant to one of the prepared surfaces, and then quickly cover with the other substrate to be bonded.

On exposure to moisture, the freshly applied material will “skin over” in about 25 minutes at room temperature and 50% relative humidity. Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula. The sealant will be tack-free in about 50 minutes.

Cure Time

After skin formation, cure continues inward from the surface. In 24 hours at room temperature and 50% relative humidity, DOWSIL™ 7094 Flowable Sealant will cure to a depth of about 2 mm. Very deep sections, especially when access to atmospheric moisture is restricted, will take longer to cure completely. Cure time is very much depending on the humidity level. It is extended at lower humidity levels and accelerated at higher levels, respectively.

Before handling and packaging bonded components, users are advised to wait a sufficiently long time to ensure that the integrity of the seal is not affected. This will depend on many factors and should be determined by the user for each specific application.

**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and
Storage**

When stored below 30°C in the original unopened containers, this product has a usable life of 12 months from the date of production.

**Packaging
Information**

DOWSIL™ 7094 Flowable Sealant is available in various standard industrial containers. Please contact your local representative for further details.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and
Environmental
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

**Disposal
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product
Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

