

# Technical data sheet



Product: 730

Manufacturer: DOWSIL

Product group: KLEBSTOFF

Article group: 1-K SILIKON

Download: 02.08.2025

## DOWSIL™ 730 FS SOLVENT RESISTANT SEALANT

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



## Technical Data Sheet

### DOWSIL™ 730 FS Solvent Resistant Sealant

Solvent resistant silicone adhesive/sealant

#### Features & Benefits

- One-component fluorosilicone adhesive/sealant.
- Cures at room temperature when exposed to moisture in the air.
- Acetoxy cure system.
- Non-sag, paste consistency.
- Easy to apply.
- Cures to a tough, flexible rubber.
- Good adhesion to many substrates.
- Stable and flexible from -65°C (-85°F) to 260°C (500°F).
- Retains its properties under exposure to fuels, oils and solvents.

#### Applications

- For bonding and sealing applications where resistance to the swelling effects of fuels, solvents and oils is required.
- For assembling and/or repairing of fuel systems and tanks.
- Used for formed-in-place gaskets where irregular shapes and harsh conditions reject ordinary seals.
- For bonding or sealing of components exposed to moisture, vibration, shock, fuels, solvents and oils for long periods of time.

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

CTM <sup>1</sup>	ASTM <sup>2</sup>	Property	Unit	Result
<b>As supplied</b>				
0176		Appearance		Non-slump paste
		Colors		White
0364		Extrusion rate <sup>3</sup>	g/minute	321
0098		Skin-over time	minutes	12
0095		Tack-free time	minutes	14
<b>Mechanical properties, cured 7 days in air at 23°C (73°F) and 50% relative humidity</b>				
0022	D792	Specific gravity		1.44
0099	D2240	Durometer hardness, Shore A		40

1. CTM: Corporate Test Method, copies of CTMs are available on request.
2. ASTM: American Society for Testing and Materials.
3. Extrusion rate: 3.2 mm orifice at 0.62 MPa., 1/8" orifice at 90 psi.

## Typical Properties (Cont.)

CTM	ASTM	Property	Unit	Result
0137A	D412	Tensile strength	MPa(psi)	3.0 (434)
0137A	D412	Elongation at break	%	195
0159A	D624	Tear strength – die B	kN/m(ppi)	11.9 (68)
		Brittle point	°C	–65
			°F	–85
0293		Peel strength, aluminum, primed	kN/m(ppi)	6.8 (39)
<b>Electrical properties, after 7 days cure in air at 25°C (77°F) and 50% relative humidity</b>				
0171		Arc resistance	seconds	124
0114	D149	Dielectric strength	volts/mil	372
0112	D150	Dielectric constant at 100 Hz		7.11
0112	D150	Dissipation factor at 100 kHz		0.007
0249	D257	Volume resistivity	Ohm.cm	5.1x10 <sup>13</sup>

## Description

DOWSIL™ 730 FS Solvent Resistant Sealant is a ready-to-use, solventless, nonslumping fluorosilicone rubber paste that reacts with moisture in the air to form a tough, rubbery solid. It is a fluid-resistant material that is ideally suited for use in many applications where resistance to fumes, splash, and sometimes even total immersion in fuels, oils and solvents is needed.

DOWSIL™ 730 FS Solvent Resistant Sealant features good resistance to weathering, vibration moisture, ozone, and temperature extremes. It retains its flexibility over a wide temperature.

DOWSIL™ 730 FS Solvent Resistant Sealant can be applied overhead or on vertical surfaces without fear of sagging, slumping or running off.

## Uses

DOWSIL 730™ FS Solvent Resistant Sealant is used primarily for bonding, sealing and caulking applications where resistance to the swelling effects of fuels, oils and solvents is needed. Other potential applications include:

- Sealing seams on various liquid storage tanks.
- Sealing fuel lines and tanks.
- Providing temporary patch for rubber linings.
- Sealing pipe joints on lines carrying solvents.
- Providing formed-in-place gaskets for sealing chemical compressors.
- Providing formed-in-place gaskets where irregular shapes and harsh conditions reject ordinary seals.
- Bonding or sealing components exposed to moisture, vibration, shock, certain fuels, oils and solvents for long periods of time.

## How to Use

### Substrate Preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion. Suitable solvents include isopropyl alcohol, acetone or methyl ethyl ketone.

Unprimed adhesion may be obtained on many substrates such as glass, metals and many common engineering plastics. Substrates to which good adhesion is normally not obtained include PTFE, polyethylene, polypropylene and related materials.

For maximum adhesion, the use of DOWSIL™ 1200 OS Primer is recommended. After solvent cleaning, a thin coat of DOWSIL™ 1200 OS Primer is applied by dipping, brushing or spraying. Allow primer to dry for 15 to 90 minutes at room temperature and a relative humidity of 50% or higher.

### How to Apply

Apply DOWSIL™ 730 FS Solvent Resistant Sealant to one of the prepared surfaces then quickly cover with the other substrate to be bonded.

On exposure to moisture, the freshly applied material will “skin-over” in about 12 minutes at room temperature and 50% relative humidity. Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula. The adhesive/sealant will be tack-free in about 14 minutes.

### Cure Time

After skin formation, cure continues inward from the surface. In 24 hours (at room temperature and 50% relative humidity) DOWSIL™ 730 FS Solvent Resistant Sealant will cure to a depth of about 3 mm. Very deep sections, especially when access to atmospheric moisture is restricted, will take longer to cure completely. Cure time is extended at over humidity levels.

Before handling and packaging bonded components, users are advised to wait a sufficiently long time to ensure that the integrity of the adhesive seal is not affected. This will depend on many factors and should be determined by the user for each specific application.

### Compatibility

DOWSIL™ 730 FS Solvent Resistant Sealant releases a small amount of acetic acid during cure. This may cause corrosion on some metallic parts or substrates, especially in direct contact or when the cure is carried out in a totally enclosed configuration which would not allow cure by-products to escape.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and Storage**

When stored at or below 32°C (90°F) in the original unopened containers, DOWSIL™ 730 FS Solvent Resistant Sealant has a usable life of 18 months from the date of production.

As DOWSIL™ 730 FS Solvent Resistant Sealant cures by reaction with moisture in air, keep the container tightly sealed when not in use. A plug of used material may form in the tip of a tube or cartridge during storage. This is easily removed and does not affect the remaining content.

**Packaging Information**

This product is available in standard industrial container sizes.

**Limitations**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

**Disposal Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

**Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

**Table I:**

Typical Fluid Resistance Values

These values are not intended for use in preparing specifications.

Fluids	Volume Swell, %	Durometer Hardness, pts change
Methanol	1.4	-4
JP-5	2.5	-5
Diesel	1.5	-5
Isopropanol	1.7	-4
JP-8	3.1	-4
DOWSIL™ OS 20 Fluid	3.6	-2

DOWSIL™ 730 FS Solvent Resistant Sealant, cured 7 days before immersion, properties obtained after 7 days immersion at room temperature.

**Table II:**

Typical Thermal Stability Properties for DOWSIL™ 730 FS Solvent Resistant Sealant

These values are not intended for use in preparing specifications.

	Exposure Time (Days)				
	0	1	3	7	14
<b>Tested at Room Temperature After Exposure at 300°F (149°C)</b>					
Durometer hardness, Shore A, points	43	44	45	45	47
Tensile strength, Mpa (psi)	2.99 (434)	3.38 (490)	3.14 (456)	3.03 (439)	2.98 (432)
Elongation, percent	195	195	177	171	159
Tear strength, kN/m (ppi)	11.91 (68)	26.97 (154)	9.63 (55)	9.11 (52)	8.93 (51)
<b>Tested at Room Temperature After Exposure at 400°F (204°C)</b>					
Durometer hardness, Shore A, points	43	43	46	47	45
Tensile strength, Mps (psi)	2.99 (434)	3.03 (439)	2.65 (385)	2.62 (381)	2.25 (327)
Elongation, percent	195	173	140	138	128
Tear strength, kN/m, (ppi)	11.91 (68)	9.28 (53)	8.76 (50)	8.41 (48)	8.06 (46)

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow  
DOWSIL™ 730 FS Solvent Resistant Sealant

© 2017–2024 The Dow Chemical Company. All rights reserved.

Form No. 80-3636-01-0424 S2D