

# Technical data sheet



Product: 1751  
Manufacturer: 3M DEUTSCHLAND GMBH  
Product group: KLEBSTOFF  
Article group: 2-K KLEBSTOFF  
Download: 02.04.2026

## 3M™ SCOTCH-WELD™ EPOXY ADHESIVE 1751 B/A

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Adhesive 1751  
B/A



[Product Details](#)



[Regulatory Info/SDS](#)

## Product Description

3M™ Scotch-Weld™ Epoxy Adhesive 1751 B/A is a gray, aluminum filled, two-part, room temperature curing structural adhesive.

## Product Features

- Excellent adhesion to metals
- Good void filling properties
- Ideal for repairing holes, dents and cracks in metal

## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Uncured Physical Properties

Attribute Name	Value
Mix Ratio by Volume (B:A)	3:2
Mix Ratio by Weight (B:A)	2:1

Attribute Name	Temperature	Value
Base Color		Gray
Accelerator Color		Amber
Base Resin		Modified Epoxy
Accelerator Resin		Modified Epoxy
Base Net Weight		10.8 lb/gal
Accelerator Net Weight		7.9 lb/gal
Base Viscosity	22 °C (72 °F)	145 s <sup>-1</sup>
Accelerator Viscosity	22 °C (72 °F)	125 s <sup>-1</sup>

<sup>1</sup> Time to deliver 20 gms@ 50 psi thru a 0.10in orifice

## Typical Mixed Physical Properties

Attribute Name	Temperature	Value
Open Time		45 min <sup>1</sup>
Worklife, 100g mixed	22 °C (72 °F)	45 min
Time to Handling Strength	22 °C (72 °F)	8 to 12 h
Time to Full Cure	22 °C (72 °F)	7 d

<sup>1</sup> Max time allowed after applying adhesive to a substrate before bond must be closed and fixed. Cure times approximate and depend on adhesive temperature. Hotmelts: The approx. bonding range of a 1/8" bead of molten adhesive on a non-metallic surface.

## Typical Physical Properties

Attribute Name	Value
Cured Color	Gray

## Typical Cured Characteristics

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Value
Shore D Hardness	ASTM D2240	77

## Typical Performance Characteristics

Substrate: Steel  
 Surface Prep: Solvent Wipe  
 Temperature: 22 °C (72 °F)  
 Dwell Time: 7 d

Attribute Name	Test Method	Value
Overlap Shear Strength	ASTM D1002	2,400 lb/in <sup>2</sup> <sup>1</sup>

<sup>1</sup> 0.035" thick substrate, 0.005" bondline. Test specimens were 1/2-inch overlap, 1-inch wide, pulled at a testing rate of .1-inch/min.

### T-Peel Adhesion

Temperature: 22 °C (72 °F)  
 Dwell Time: 7 d  
 Test Method: ASTM D1876

Substrate	Surface Prep	Value
FPL Etched Aluminum		4 lb/in width <sup>1</sup>
Steel	Solvent Wipe	5 lb/in width <sup>1</sup>

<sup>1</sup> 2 psi applied during dwell

## Handling/Application Information

### Directions for Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user. See surface preparation section.
  2. Use gloves to minimize skin contact with adhesive.
  3. This product consists of two parts. Mix thoroughly by weight or volume in the proportions specified in the Uncured Properties Section. Mix approximately 15 seconds after a uniform color is obtained.
  4. For maximum bond strength, apply product evenly to both surfaces to be joined.
  5. Application to the substrates should be made within 45 minutes. Large quantities and/or higher temperatures will reduce this working time.
  6. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until firm. Up to 200°F (93°C), will speed curing.
  7. The following times and temperatures will result in a full cure:  
 Cure Temperature Time  
 75°F (24°C) 7 days  
 150°F (67°C) 120 minutes  
 200°F (93°C) 30 minutes
  8. Keep parts from moving until handling strength is reached. Contact pressure is necessary. Maximum shear strength is obtained with a 3-5 mil bond line.
  9. Excess uncured adhesive can be cleaned up with ketone type solvents.\* Adhesive coverage: A 0.005 in thick bondline will yield a coverage of 320 sqft/gallon.
- \*Note: When using solvents, extinguish all ignition sources and follow manufacturer’s precautions and directions for use.

### Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user.

**The following cleaning methods are suggested for these common surfaces:**

#### Steel:

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.\*
  2. Sandblast or abrade using clean fine grit abrasives.
  3. Wipe again with solvent to remove loose particles.
  4. If a primer is used, it should be applied within 4 hours after surface preparation.
- \*Note: Read and follow component supplier's environmental, health and safety recommendations prior to preparing this etch solution.

#### **Aluminum:**

1. Vapor Degrease: Perchloroethylene condensing vapors for 5-10 minutes.\*
2. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 3°C).  
Sodium Dichromate 4.1-4.9 oz./gallon  
Sulfuric Acid, 66°Be 38.5-41.5 oz./gallon  
2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum  
Tap Water as needed to balance
4. Rinse: Rinse panels in clean running tap water.
5. Dry: Air dry 15 minutes; force dry 10 minutes at 190°F (88°C) ± 10°F (5°C).
6. If primer is to be used, it should be applied within 4 hours after surface preparation.

#### **Plastics/Rubber**

1. Wipe with isopropyl alcohol.\*
2. Abrade using fine grit abrasives.
3. Wipe again with isopropyl alcohol.\*

#### **Glass**

1. Solvent wipe surface using acetone or methyl ethyl ketone (MEK).\*
2. Apply a thin coating (0.0001 in. or less) of primer such as 3M™ Scotch-Weld™ Structural Adhesive Primer EC-3901 to the glass surfaces to be bonded and allow the primer to dry before bonding.

\*Note: When using solvents, extinguish all ignition sources and follow manufacturer's precautions and directions for use

## **Storage and Shelf Life**

Store products at 60-80°F (15-27°C) for maximum storage life.

Rotate stock on a "first in-first out" basis. 3M™ Scotch-Weld™ Epoxy Adhesive 1751 B/A has a storage life of 24 months from date of manufacture in unopened containers.

## **Precautionary Information**

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

## **Automotive Disclaimer**

**Select Automotive Applications:** This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M  
Industrial Adhesives and Tapes Division  
3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550

3M and Scotch-Weld are trademarks of 3M Company.  
©3M 2022 (5/22)