

Technical data sheet



Product: 9080

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: DOPPELSEITIG

Download: 22.12.2024

9080HL DOUBLE COATED SPLICING TAPE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708



9080HL Double Coated Splicing Tape

Temporary Product Data Sheet

Updated : May 2000
Supersedes : New

Product Description 9080HL is a Double Coated Non-woven Tape with Polycoated Paper Liner.

Physical Properties
Not for specification purposes

| | |
|---|--|
| Adhesive Type | Cross linked, Tackified Acrylic Adhesive |
| Carrier Type | Non-woven |
| Thickness (ASTM D-3652) Tape Release Liner | 0.160 mm 0.160 mm |
| Normal Tolerance | 15 % |
| Release Liner | Polycoated Paper Liner – 3M Logo Printed |
| Tape Colour | White |
| Shelf Life | 12 months from date of manufacture by 3M when stored in the original carton at room temperature & 50 % Relative Humidity |

Performance Characteristics
Not for specification purposes

| | |
|--|--|
| Peel Strength (ASTM-D3330) 180° Peel Adhesion; Room Temperature 72 hour ageing, Jaw Speed : 305 mm/min; with A1 Strip. | 7.5 N/10mm. |
| Static Shear (ASTM-D3654) 500 grams loading on stainless steel 6.45 cm ² overlap at room temperature. | 10,000 min |
| Liner Release 1 inch (25.4mm) width Jaw Speed : 12 inches/min (305mm / min) | Max. 50 grams |
| Hot Splicing (BTM 220) 1Kg/sq.in (1.25Kg/30mm x 25mm test area), overlap shear, held for 60 seconds | In excess of 170°C (test program on-going) |
| Bonding strength | Delaminates most papers |
| Instant adhesion | Excellent (for flying splices) |

Date : May 2000
 9080HL Double Coated Splicing
 Tape

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength. For splicing applications, rubbing down the tape prior to removing the liner to expose the splicing adhesive will improve the splice performance. Ideal tape application temperature range is 21°C to 38°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive may become too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Applications

9080HL tape is specially formulated for low- and high-speed splicing applications, followed if required by heat-setting or other oven-based processing conditions. The tape makes an excellent bond to paper and board, and many plastic film substrates including Polyethylene, Polypropylene and PVC.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC
 3M House,
 28 Great Jackson Street,
 Manchester,
 M15 4PA

Product Information :
 Tel 0870 60 800 50
 Fax 0870 60 700 99

3M Ireland
 3M House, Adelphi Centre,
 Upper Georges Street,
 Dun Laoghaire, Co. Dublin,
 Ireland

Customer Service :
 Tel (01) 280 3555
 Fax (01) 280 3509
