

# Technical data sheet



Product: AC-160

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBSTOFF

Article group: PRIMER

Download: 10.06.2025

## 3M™ ADHESION PROMOTER AC-160

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708

## 3M™ Adhesion Promoter AC-160

AC-160 is a waterborne adhesion promoter for bonding polysulfide sealants to a variety of metal, composite, and solvent-sensitive substrates. A blend of water and coupling agent, AC-160 accelerates adhesion development and enhances sealants' ability to bond to aged or low-energy surfaces.



### Surface Preparation

For best results, dirt, grease, oils, fingerprints, etc., should be removed from surfaces to be bonded by solvent wiping just prior to application of adhesion promoter. Use clean solvent that is compatible with the substrate and clean, approved cloths, such as those specified by AMS3819. Carefully pour solvent onto the cloth to avoid contaminating the solvent supply. Clean only a small area at a time, quickly wiping it dry with another clean cloth before the solvent evaporates. Turn cleaning cloth frequently to prevent redeposition of contaminants.

### Benefits

- Compatible with 3M Aerospace polysulfide sealants
- Accelerates adhesion of sealants to metal, composite, and coated substrates.
- Waterborne formula for surfaces that are sensitive to organic solvents
- Enables more robust adhesion of sealants to challenging substrates
- One component product for easy application

### Physical & Performance Properties

<b>Color</b>	Pink
<b>180° Peel Strength*</b>	
<b>Substrate</b>	<b>Typical Value</b>
AMS-C-27725 TY 2 (Polyurethane) AMS2629 TY 1 JRF / 3% NaCl 7 days, 140°F (60°C)	68 lbf/in (299 N/25 mm) 100% Cohesive
AMS-C-27725 TY 2 – Aged Non-immersed	66 lbf/in (288 N/25 mm) 100% Cohesive
AMS-C-27725 TY 2 - Aged AMS2629 TY 1 JRF / 3% NaCl 7 days, 140°F (60°C)	68 lbf/in (299 N/25 mm) 100% Cohesive
AMS4911 (Titanium) AMS2629 TY 1 JRF / 3% NaCl 7 days, 140°F (60°C)	59 lbf/in (257 N/25 mm) 100% Cohesive
MIL-PRF-23377 (Epoxy Primer - solvent) 3% Aqueous NaCl 7 days, 140°F (60°C)	64 lbf/in (282 N/25 mm) 100% Cohesive
MIL-PRF-85582 (Epoxy Primer - water) 3% Aqueous NaCl 7 days, 140°F (60°C)	65 lbf/in (286 N/25 mm) 100% Cohesive

\* In accordance with specification AMS3100, Class 3

## Application Instructions

3M™ Adhesion Promoter AC-160 may be applied to clean, dry surfaces with a gauze, cloth, or brush. AC-160 should be applied sparingly to the surface to produce a transparent and uniform pink tint. Excess adhesion promoter should be wiped off while still wet with a clean cloth or gauze. Allow adhesion promoter to air dry for 15 - 30 minutes before applying sealant. For best results, apply sealant to the adhesion promoted surface within 4 hours. If sealant is not applied within 24 hours, reclean the surface and reapply the adhesion promoter.

## Shelf Life and Storage

The shelf life of 3M™ Adhesion Promoter AC-160 is 6 months from date of packaging, when stored between 40°F (4.4°C) and 80°F (27°C) in the original unopened containers. AC-160 is waterborne and should not be exposed to freezing conditions. The product should not be used if it appears cloudy.

*Note: The shelf life and storage conditions listed in this Technical Data Sheet are based on product capability and align with the 3M Standard internal specification. Other industry and/or OEM specifications to which the product is qualified may establish different storage requirements. The information shown on the product label and/or the accompanying Certificate of Analysis (COA) takes precedence over the Technical Data Sheet.*

**Precautionary Information:** Refer to Product Label and Safety Data Sheet for health and safety information before using this product. For additional health and safety information, visit [www.3m.com/3M/en\\_US/company-us/SDS-search/](http://www.3m.com/3M/en_US/company-us/SDS-search/)

**Authorization to Use:** Ensure products meet all applicable specifications, standards, and maintenance manual requirements for the platform being worked on and validate all aircraft approvals against current technical documentation.

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



**Automotive & Aerospace Solutions Division**  
3M Center  
St. Paul, MN 55144-1000  
Phone 1-800-235-2376  
Web [www.3M.com/aerospace](http://www.3M.com/aerospace)

160  
Issue date: 11/2022

3M is a trademark of 3M Company  
© 3M 2022. All rights reserved.