Technical data sheet



Product:	2000
Manufacturer:	3M DEUTSCHLAND GMBH
Product group:	KLEBEBAND
Article group:	EINSEITIG
Download:	31.08.2025

## SCOTCH<sup>®</sup> 2000<sup>™</sup> ELECTRICIAN'S DUCT TAPE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH Industriestraße 15 D-75382 Althengstett Fax:

Telephone: E-Mail: +49(0)7051/9297-0 Website: +49(0)7051/9297-99 www.tewipack.de

info@tewipack.de

Managing director: Alexander Uhl, Michael Uhl HRB 330424 Amtsgericht Stuttgart 85

Bank details: Sparkasse Pforzheim Calw BLZ 666 500 Konto 17 787

Commerzbank Sindelfingen BLZ 603 400 71 Konto 8 001 166

Vereinigte Volksbank AG Böblingen BLZ 603 900 00 Konto 80 089 003

Postbank Stuttgart BLZ 600 100 70 Konto 146 294 708



# Scotch<sup>®</sup> 2000<sup>™</sup>

Electrician's Duct Tape

## 1. **Product Description**

Scotch<sup>®</sup> 2000 Electrician's Duct Tape is a water resistant duct tape with a polyvinyl chloride (PVC) backing and a rubber adhesive. Scotch<sup>®</sup> 2000 is designed to be an electrician's utility tape for holding and bundling applications.

- Easy tear
- No cloth-does not absorb water.
- Clean removal (minimal residue)
- Not recommended for sealing air ducts.

## 2. Typical Properties

Properties measured at room temperature 23°C unless otherwise stated.

Physical Properties	Typical Value
Color	Grey
Thickness ASTM D1000	0,15 mm
Adhesion to Steel ASTM D1000	2,19 N/10 mm.
Tensile Strength ASTM D1000	21,02 N/10 mm
Elongation at Break ASTM D1000	100%

Note: These are typical properties and should not be used for specification purposes.

Reference: AABBCC28219\_02

Issue date 02.11.2016

© 3M 2014 All Rights Reserved.

Template-EMD-EU-1Column Dec.2015

## 3. User Information

#### 3.1 Agency Approvals & Self Certifications

• For RoHS information, please visit www.3M.com/RoHS

#### 3.2 Shelf Life & Storage

Scotch® 2000 has a three year shelf life (from date of manufacture) when stored under the following recommended storage conditions. Store behind present stock in a clean, dry place at a temperature of 21°C and 40-50% relative humidity. Good stock ro tation is recommended.

#### 3.3 Availability

Please contact your local distributor.

### 4. Additional Information

To request additional product information see address below.

#### Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

Values presented have been determined by standard test methods and are average values not meant to be used for specification purposes.

All questions of warranty and liability relating to 3M products are governed by the terms of the respective sale subject, where applicable, to the prevailing law.

3M is a trademark of the 3M Company.

Insert Company address before issue Reference: AABBCC28219\_02

Issue date 02.11.2016

© 3M 2014 All Rights Reserved.

Template-EMD-EU-1Column Dec.2015