

Technisches Datenblatt



Produkt: 2181-1

Hersteller: BOSTIK SA

Warengruppe: KLEBSTOFF

Artikelgruppe: UV- AUSHÄRTENDER KLEBSTOFF

Download: 19.05.2025

POLYTEC UV 2181-1

Dieses Datenblatt wurde Ihnen von der Firma tewipack Uhl GmbH zur Verfügung gestellt. Die Firma tewipack Uhl GmbH übernimmt keinerlei Verantwortung für die Aktualität und die Richtigkeit der enthaltenen Informationen. Die Eigenschaften der Produkte können sich aufgrund verschiedener Einflüsse wie beispielsweise Zusammensetzung und Zustand des Substrats, Unreinheiten in oder auf dem Substrat, Temperatur und Luftfeuchtigkeit bei der Lagerung und Umgebungsbedingungen während der Anwendung ändern. Bei Verwendung dieses Produkts in Kombination mit anderem Material ist der Kunde dafür verantwortlich, durch eigene Tests zu prüfen, ob das Produkt für die geplante Kombination geeignet ist und ob diese Kombination die erwarteten Ergebnisse liefert

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telefon:
+49(0)7051/9297-0
Telefax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Internet:
www.tewipack.de

Geschäftsführer:
Alexander Uhl, Michael
Uhl
HRB 330424
Amtsgericht Stuttgart

Bankverbindungen:
Sparkasse
Pforzheim Calw
BLZ 666 500 85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089 003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146 294
708

Polytec UV 2181-1

Description

- one-component acrylate/methacrylate hybrid
- solvent-free
- UV/VIS curing

Product properties

- very fast curing
- medium viscous
- slightly thixotropic
- very good adhesion to thermoplastic substrates
- flexible
- impact resistant

Special features

- no stringing

Applications

- bonding, sealing, potting

Processing information

After application, the joining of the parts should be done quickly, as some products already cure with daylight. Any contact of the adhesive with base metals, contamination with amines or reducing agents (e.g. vitamin C) should be strictly avoided, as this may lead to undesired premature curing of the product (e.g. in the metering unit).

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other contaminants in order to obtain an optimum and reproducible bond. For lightly soiled parts, wiping with isopropanol or ethanol is sufficient. Substrates that have a low surface energy (e.g. polyethylene, polypropylene, Teflon) must be physically pretreated (e.g. with atmospheric plasma or corona) to achieve sufficient adhesion.

Polytec UV 2181-1

UV-light curing acrylate/ methacrylate adhesive

Technical Information

Polytec UV 2181-1

Properties in the uncured state	Method	Unit	Technical data
Chemical base	-	-	acrylate/methacrylate hybrid
Color	-	-	colorless, transparent
Number of components	-	-	1
Shelf life at max. 25°C	-	Month	6
Consistency	-	-	medium viscous, thixotropic
Density	-	g/cm ³	app. 1.05
Viscosity rheometer, cone/plate	400 s ⁻¹ at 23°C 10 s ⁻¹ at 23°C	mPa·s	app. 320 app. 1,160

Properties in the cured state	Method	Unit	Technical data
Shore-hardness	Shore D curing at 395 nm*	-	53
Service temperature	-	°C	-40 / +80
Max. temperature short term	-	°C	app. +250
Lap shear strength PC/PC PMMA/PMMA PC/PA6.6 PET/PET	curing at 395 nm*	N/mm ²	4.3 6.6 5.3 4.9
Compressive shear strength glass/glass	curing at 395 nm*	N/mm ²	10.5
Tensile strength	curing at 395 nm*	N/mm ²	10.1
Elongation at break	curing at 395 nm*	%	320
Water absorption 24 hrs. 23°C 85°C	gravimetric, curing at 395 nm*	%	1.7 3.8

*For some products, the through-curing is limited in 3 mm or by substrates, therefore the curing time for the determination of the measured value is adjusted individually.

Polytec UV 2181-1

Curing*	Method	Unit	Technical data
Feasible UV-wavelength range	-	nm	365 - 405
Optimum wavelength range for curing	-	nm	395 - 405
Curing dose at 395 nm in 1 mm layer	-	mJ/cm ²	1,800
Curing time at 1,500 mW/cm ² @395 nm in 1 mm layer	-	sec	app. 1-2

*High-power LED lamps are recommended for curing in order to introduce the optimum dose and wavelength with the highest possible energy yield and the lowest possible temperature load on the substrate.

Work and health protection

See safety data sheet.

For your attention:

The above data can only be general information. The properties and performance characteristics listed are typical values and do not form part of the product specification. Due to the processing and application conditions beyond our control and the large number of different materials, we recommend that you first carry out your own tests. Therefore, no liability for concrete application results can be derived from the information and notes in this data sheet. With the publication of this edition, all previous technical data sheets become invalid.

Polytec PT GmbH
Polymere Technologien

Ettlinger Straße 30
76307 Karlsbad
Germany
Phone +49 (0)7202 706-3500
info-pt@bostik.com
www.polytec-pt.com

Polytec PT GmbH
Polymere Technologien
Plant Maxdorf
Bahnhofstr. 1
67133 Maxdorf
Germany

info-pt@bostik.com
www.polytec-pt.com