

# Technical data sheet



Product: 235

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: ELEKTRO

Article group: VERGUSSMASSE

Download: 07.12.2025

## 3M™ SCOTCHCAST™ ELECTRICAL RESIN 235

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708



# Scotchcast™ Electrical Resin 235

Two-Part, Oven-Curing, Class B, Semiflexible, Unfilled Epoxy Liquid Resin

## Data Sheet

### Product Description

3M™ Scotchcast™ Electrical Resin 235 system has permanent semiflexibility, thermal shock and impact resistance, good electrical and adhesion properties. This low-viscosity resin is well suited to a variety of general purpose, Class B (130°C) applications. Its low viscosity and good wetting characteristics allow complete impregnation of even small coils, and it has the mechanical strength and flexibility needed for high-quality insulation of large castings, such as motors, transformers and coils.

- Low viscosity
- Class B (130°C)
- Good flexibility

### Handling Properties

Mix Ratio (A:B)	Wt 1:2
	Vol (%) 31:69
Viscosity	A = 13,000 cps
	B = 1,000 cps
	Mixed = 1,500 cps
Density	A = 1.15 kg/l (9.60 lbs/gal)
	B = 1.02 kg/l (8.51 lbs/gal)
Flash Point	A = 205°C (400°F)
	B = 177°C (351°F)
Gel Time	18 min. at 120°C
Curing Guide	75°C (167°F) 15-20 hrs
	95°C (203°F) 6-8 hrs
	120°C (248°F) 2-3 hrs

### Test Methods

<sup>1</sup> 3M Test Method	<sup>5</sup> Fed. Std. No. 406, Method 1031
<sup>2</sup> MIL-I-16923E	<sup>6</sup> Fed. Std. No. 406, Method 4021
<sup>3</sup> Fed. Std. No. 406, Method 1021	<sup>7</sup> Fed. Std. No. 406, Method 4041
<sup>4</sup> Fed. Std. No. 406, Method 1011	

### Typical Data/Physical Properties

Property	Value
Color	Brown
Hardness (Shore D)	55
Specific Gravity (cured)	1.10
Compressive Strength <sup>3</sup>	1300 psi
10% Compression	(91 kg/cm <sup>2</sup> )
Tensile Strength <sup>4</sup>	1300 psi
(1/8" x 1/2" Sample)	(91 kg/cm <sup>2</sup> )
Elongation <sup>4</sup> (% at break)	75
Flexural Strength <sup>5</sup>	3200 psi
(1/2" x 1/2" Sample)	(225 kg/cm <sup>2</sup> )
Thermal Conductivity <sup>2</sup>	4.0x10 <sup>-4</sup>
(Cal/sec/cm <sup>2</sup> /°C/cm)	
Coefficient of Linear Thermal Expansion <sup>2</sup>	
(23°C to 113°C) (length/unit length/°C)	16x10 <sup>-5</sup>
Electric Strength <sup>2</sup>	325 volts/mil
(1/8" [3.175 mm] Sample)	12,800 volts/mm
Thermal Shock <sup>1</sup>	Pass
10 Cycles -55°C to 130°C 1/8" (3.175 mm) Olyphant Insert	
Thermal Shock <sup>2</sup>	Pass
Mechanical Shock Resistance <sup>2</sup>	7.8
(Weight in lbs. of ball causing fracture)	
Moisture Absorption <sup>2</sup>	.92
% weight increase, 240 hrs. @ 96% R.H.	
Water Immersion	
(sample cured 3 hrs. @ 120°C, 1000 hrs. @ 23°C) % weight gain	1.3
Thermal Aging	
(2 1/4" x 2 1/4" x 1/8" sample, 1000 hrs. at 130°C) % weight loss	4.4
Hardness Change (Shore D)	+6
Dielectric Constant <sup>6</sup> (100 cycles @ 23°C)	4.25
Dissipation Factor <sup>6</sup> (100 cycles @ 23°C)	.07
Volume Resistivity <sup>7</sup> (ohm-cm @ 23°C)	2.9 x 10 <sup>14</sup>
Thermal Aging	
(2 1/4" x 2 1/4" x 1/8" sample, 1000 hrs. at 155°C) % weight loss	18.7
Hardness Change (Shore D)	+33
Dielectric Constant <sup>6</sup> (100 cycles @ 23°C)	4.75
Dissipation Factor <sup>6</sup> (100 cycles @ 23°C)	.05
Volume Resistivity <sup>7</sup> (ohm-cm @ 23°C)	3.2 x 10 <sup>14</sup>

**Note:** These are typical values and should not be used for specification purposes.

## Usage Information

### Mixing

Mix the separate parts before removing them from their containers. They may be warmed to 60°C (140°F) to aid mixing. Weigh the correct proportions of the separate parts to within 2% accuracy and combine them. Thoroughly blend the mixture until the color is absolutely uniform or a homogeneous mixture is obtained.

### Deaerating

Entrapped air can be removed by evacuating for 5 to 15 minutes at 5 to 10 mm of mercury (Hg) absolute pressure. Warming the 3M™ Scotchcast™ Electrical Resin to 60°C (140°F) facilitates this process. Container side walls should be four times the height of liquid resin to contain the foaming that takes place under vacuum.

### Casting and Impregnating

Pour the warm resin into the preheated 100°C mold. If no mold is used, dip the preheated part into the resin. Heating the resin and mold aids impregnation. For maximum impregnation, evacuate for 5 to 15 minutes at 5 mm of mercury (Hg) absolute pressure, or pour under vacuum and hold for several minutes before releasing.

### Curing


Where minimum stress and maximum thermal shock resistance are required, the lower temperature cure cycle is recommended. (See “Curing Guide” of **Handling Properties** section). Time should be added to the cure cycle to allow the resin to reach the curing temperature.

### Storage


Both parts of this resin system should be stored at temperatures between 20 to 30 degrees Celsius, and 30% to 60% relative humidity. When not in use, containers should be kept tightly closed. Storage at conditions outside those suggested may compromise the performance of the resin.

## Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid statements found in the Material Safety Data Sheet (MSDS) and/or product label of chemicals prior to handling or use.




Brookfield Viscosity vs Time @ 170°F (77°C) and 200°F (93°C)




Brookfield Viscosity vs Time @ 73°F (23°C)


**Dissipation Factor**  
Fed. Std. No. 406, Method 4021  
(Test Frequencies in Hertz)



**Dielectric Constant**  
Fed. Std. No. 406, Method 4021  
(Test Frequencies in Hertz)



**Volume Resistivity (ohm-cm)**  
Fed. Std. No. 406, Method 4041



3M and Scotchcast are trademarks of 3M Company.

#### Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

**Warranty; Limited Remedy; Limited Liability.** This product will be free from defects in material and manufacture for a period of one (1) year from the date of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, **3M will not be liable for any loss or damage arising from this 3M product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.**



#### Electrical Markets Division

6801 River Place Blvd.  
Austin, TX 78726-9000  
800/676-8381  
Fax: 800/828-9329  
[www.3M.com/electrical/oem](http://www.3M.com/electrical/oem)



*Printed on 50% recycled paper  
with 10% post-consumer*

Litho in USA  
© 3M 2004 78-8124-5591-9-B