

# Technical data sheet



Product: 1436

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: EINSEITIG

Download: 01.06.2025

## 3M™ ALUMINIUM FOIL TAPE 1436 & 1436P

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH  
Industriestraße 15  
D-75382 Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank details:  
Sparkasse  
Sindelfingen  
Pforzheim  
Calw  
BLZ 666 500  
85  
Konto 17 787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001 166

Vereinigte  
Volksbank AG  
Böblingen  
BLZ 603 900 00  
Konto 80 089  
003

Postbank  
Stuttgart  
BLZ 600 100  
70  
Konto 146  
294 708

# 3M™ Aluminium Foil Tape 1436 & 1436P



## Product description

An aluminium foil combined with a rubber adhesive and an easy release liner designed for holding and sealing on a variety of surfaces. 1436 and 1436P meet low flammability rating according to DIN 4102B1.

- Foil backing provides reflective surface for both heat and light.
- Rubber adhesive bonds to many surfaces.
- Low water vapor transmission rate offers good sealing and patching performance.
- Best results obtained when applied to clean dry surfaces above 0 °C.
- Performance range is from –25 °C to +70 °C; short term up to 100 °C.



## Physical properties

	1436	1436P
Adhesive type	Synthetic Rubber	
Backing	Soft Aluminium	
Backing Thickness	0,025 mm	
Total Tape Thickness (without liner)	0,065 mm	
Liner	0,055 mm siliconized glassine white paper liner	0,065 mm siliconized white paper liner



## Typical performance characteristics

Property	Values
Adhesion to steel after 72 hour dwell at room temperature according to AFERA 5001	9,5 N / 10 mm
Tensile strength according to AFERA 4005	18 N / 10 mm
Elongation at break according to AFERA 4005	6%
Water vapour transmission Rate	< 1.0 g/m² x 24 h
Flammability rating according to DIN 4102 <i>Reference PA-111 2-216</i>	B1
Fire protection class acc. to EN 45545-2/2016 <i>Reference 2000488</i>	R1 / HL3; R7 / HL3



## Storage and shelf life

- Store in the original packaging.
- Avoid direct sunlight and other UV-light and heat sources.
- Ideal conditions are 20 °C and 50% relative humidity

If stored properly, product retains its performance and properties for 12 months from the date of manufacturing.

## Further technical data

3M can offer extended data for different test conditions and substrates. Please get in touch with your 3M Sales Rep or Application Engineer.

**Trademarks:** 3M is a trademark of 3M Company.

**For additional information:** To request additional product information or to arrange for sales assistance, please contact your local 3M organization.

**Select Automotive Applications:** This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

**Important notice:** All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

### 3M United Kingdom PLC

2M Centre, Cain Road, Bracknell  
RG12 8HT  
United Kingdom

### 3M Ireland Ltd

The Iveagh Building, 3rd Floor  
The Park, Carrickmines 18  
Ireland

### 3M Belgium bvba/ sprl

Hermeslaan 7  
1831 Diegem  
Belgium

### 3M Svenska AB

Herrjärva torg 4  
170 67 Solna  
Sweden

### 3M Nederland B.V.

Molengraaffsingel 29  
2629 JD Delft  
The Netherlands

### 3M a/s

Hannemanns Allé 53  
DK-2300 Copenhagen S.  
Denmark

### 3M Norge AS

Tærudgata 16  
2004 Lillestrøm  
Norway

### Suomen 3M Oy

Keilaranta 6  
02150 Espoo  
Finland