Technical data sheet



Product: 3430

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: **KLEBEBAND**

Article group: **EINSEITIG**

Download: 15.12.2025

SCOTCH™ TAPE 3430

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

3M Scotch[™] Tape 3430

High Performance Auto Refinish Tape

Product Information

12/95

Product Description / Markets

Scotch[™] Tape 3430 is a brown colored creped paper masking tape for high quality performance auto refinishing masking.

Features	Advantages	Benefits
* Latex saturated heavy weight creped paper backing	* Excellent solvent resistance	* Prevents paint bleed through
	* Good water resistance	* No need to re-mask after wet sanding
		* Performs well with water based paint systems
	* Good conformability	* Better curve masking
	* Excellent edge tear resistance	* Prevents tearing in curves or on difficult surfaces
	* Excellent sliver resistance	* Easy removal
	* Easy hand tear	* Better handling
* Controlled crosslinked rubber resin adhesive	* Excellent instant adhesion	* Sticks easily
	* Excellent holding power	 Resists lifting even in repeat bake cycles
	* Good adhesive transfer resistance	* Clean removal
	* Controlled unwind	* Easy handling

Applications / Performance

The excellent temperature performance of 110 °C for one hour of the ScotchTM Tape 3430 allows higher curing temperatures with infrared or heat lamps and for longer and repeat bake cycles.

Scotch[™] Tape 3430

Product Characteristics

Thickness : 0.175 mm AFERA 4006 Adhesion to steel : 10 N/25 mm AFERA 4001 Tensile strength : 110 N/25 mm AFERA 4004 Elongation : 10.5 % AFERA 4005

Temperature performance : 110 °C

Satisfactory performance and clean removal of ScotchTM Tape 3430 will be achieved at varying temperatures/time exposure on many substrates. Tests should be conducted to establish ScotchTM Tape 3430 performance parameters in your process conditions. The optimum level for product performance and easy removal is at 110 °C for 60 min.

Available Sizes

Width (mm) : 9, 12, 15, 19, 25, 30, 38, 50, 75 and 100

Length (m) : 50

Storage Conditions

Store in clean dry place. Temperature of 21 °C and 50 percent relative humidity are recommended.

Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. Please ensure before using our products that it is suitable for your intended use. All questions of liability relating to this products are governed by the Terms of Sale subject, where applicable, to the prevailing law.

Masking and Packaging Systems Division

3M Europe Masking & Packaging Systems Division Hermeslaan 7 B - 1831 Diegem

Tel: ++32-2-722.45.50 Fax: ++32-2-722.45.18