

Technical data sheet



Product: 4225

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: KLEBEBAND

Article group: DOPPELSEITIG

Download: 27.06.2026

3M ACRYLIC FOAM KLEBEBAND 4225

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

3M™ Acrylic Foam Tape 4225

Technical Data Sheet



Description

3M™ Acrylic Foam Tape 4225 is a 3.18 mm (0.125 in) thick, white, double-coated acrylic foam tape used in a variety of automotive applications where bonding surface contours are poorly matched and a thick foam is required.


Product features of 3M AFT 4225 include:

- Unique foam core that provides stress relaxation when high application loads are encountered, while maintaining tight bond-line aesthetics under normal conditions.
- Bonds to a variety of automotive substrates.
- Provides high final adhesion and peel strength.

The acrylic foam core of 3M AFT 4225 has unique viscoelastic properties that allow it to elongate and relax when put under load, minimizing stress on the adhesive bond line. 3M AFT 4225 has AR5 adhesive on both sides of the foam for bonding to a variety of automotive substrates. Since product performance will depend on actual conditions within a specific application, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular material purpose and suitable for the user's method of application.

Potential applications of 3M AFT 4225 are the attachment of roof ditch moldings, claddings, appliques, and body side molding.

Product Construction



Liner Options

See the technical update [“3M™ Acrylic Foam and Acrylic Plus Tapes: Product Constructions”](#) for liner and tabbing information.




Physical Properties

4225	
Thickness Range	3.18 mm ±0.30 mm (0.125 in ±0.012 in)
Density Range	576 kg/m ³ ±80 kg/m ³ (36 lb/ft ³ ±5 lb/ft ³)

Performance Properties

Typical performance of 3M™ Acrylic Foam Tape 4225 is shown below. Peel and shear values depend on plastic substrate characteristics and/or paint composition. These values are for reference only.

Breakaway and Continuous Peel

 <p>Test Bar Painted Panel</p>	72 hrs at 22°C (72°F)	Breakaway Peel	120 N/12.7 mm	(27 lbs/.5 in)
		Continuous Peel	62 N/12.7 mm	(14 lbs/.5 in)
 <p>Breakaway</p>	72 hrs at 70°C (158°F)	Breakaway Peel	156 N/12.7 mm	(35 lbs/.5 in)
		Continuous Peel	89 N/12.7 mm	(20 lbs/.5 in)
 <p>Continuous Peel</p>	72 hrs at 38°C /100% RH (100°F/100%RH)	Breakaway Peel	89 N/12.7 mm	(20 lbs/.5 in)
		Continuous Peel	49 N/12.7 mm	(11 lbs/.5 in)

Breakaway and continuous peel tests are run with 12.7 mm (0.5 in) wide tape on PVC test bars. Tests were run on base coat/clear coat paint at a separation rate of 305 mm/min (12 in/min).

Static Shear

Exceeds 100 hours at 70°C (158°F). Static shear tests are run with 12.7 mm (0.5 in) wide by 50.8 mm (2 in) long tape on PVC test bars, 6.8 kg (15 lbs) roll-down against stainless steel. Static weight is 250 gm (0.55 lbs).



Shelf Life

36 months from date of manufacture when stored at 4°C–38°C (40°F–100°F) and 0–95% relative humidity. The optimum storage conditions are 22°C (72°F) and 50% relative humidity.

Regulatory Information

Please refer to the product label and Safety Data Sheet (SDS) for health and safety information before using. Observe proper handling precautions as outlined in the SDS, which is available on request or at www.3M.com/msds.

The product is published as a material entry and is available for access on www.mdssystem.com. For product IMDS I.D. number, email requests to 3M-IMDSrequest@mmm.com.

Contact Information

The information provided in this technical document is intended as a guide for this product. For more information or help in selecting a 3M product for an application, please contact your 3M technical service representative or call 1-800-328-1684.

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information. **Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property. **Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. **Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



Automotive and Aerospace Solutions Division
3M Center
St. Paul, MN 55144-1000
1-800-328-1684
3M.com/autosolutions

3M is a trademark of 3M Company. Please recycle.
Printed in USA. © 3M 2020. All rights reserved.