

# Technical data sheet



Product: 419E - Flüssig

Manufacturer: MG CHEMICALS

Product group: ELEKTRO

Download: 16.04.2026

## 419E LIQUID

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl  
GmbH  
Industriestraße  
15  
D-75382  
Althengstett

Telephone:  
+49(0)7051/9297-0  
Fax:  
+49(0)7051/9297-99

E-Mail:  
info@tewipack.de  
Website:  
www.tewipack.de

Managing  
director:  
Alexander Uhl,  
Michael Uhl  
HRB 330424  
Amtsgericht  
Stuttgart

Bank  
details:  
Sparkasse  
Pforzheim  
Calw  
BLZ 666  
500 85  
Konto 17  
787

Commerzbank  
Sindelfingen  
BLZ 603 400 71  
Konto 8 001  
166

Vereinigte  
Volksbank  
AG  
Böblingen  
BLZ 603 900  
00  
Konto 80  
089 003

Postbank  
Stuttgart  
BLZ 600  
100 70  
Konto 146  
294 708

# 419E Liquid



## Premium Acrylic Conformal Coating

419E is a 1-part, UL 746E certified, acrylic conformal coating. It cures to a durable, flexible and smooth finish. It is easy to apply and can be handled in 15 minutes. It may be removed with appropriate strippers, or soldered through for repair or rework.

419E creates a robust moisture barrier that protects printed circuit boards in humid environments. It provides strong protection against moisture, corrosion, fungus, dirt, dust, thermal shock, short circuits, high-voltage arcing, and static discharge.

## Features & Benefits

Certified UL 746E (File# E203094)

Certified IPC-CC-830C

Xylene and toluene free

Fluoresces under UV-A light

Suitable for use with selective coating equipment

## Cure Instructions

Allow to dry at room temperature for 24 hours, or after letting sit for 15 minutes, cure the coating in an oven at one of these time/temperature options:

Temperature	65 °C	80 °C	100 °C
Time	30 min	15 min	5 min

## Storage and Handling

Store between -5 and 27 °C in a dry area, away from sunlight (see SDS).



## Available Packaging

Part #	Packaging	Net Vol.	Net Wt.
419E-1L	Can	945 mL	830 g
419E-4L	Can	3.78 L	3.32 kg
419E-20L	Pail	18.9 L	16.6 kg

# 419E Liquid



## Liquid Properties

Binder System	Acrylic	—
Dry Time to Handle	15 min (1 coat) 25 min (2 coats)	—
Minimum Recoat Time	3 min	—
Recommended Film Thickness	25–75 $\mu\text{m}$	—
Density	0.9 g/mL	ASTM D1475
Viscosity @ 25 °C	160 cP	Brookfield Engineering labs Inc. IPCTM-65- Method 2.4.24.4
Percent Solids	29%	—
Theoretical Coverage @ Recommended Thickness	93 176 $\text{cm}^2/\text{L}$	Calculated
Calculated VOC	625 g/L	—
Shelf Life	5 y	—

## Cured Properties

UL	746E	—
IPC-CC-830	C revision	—
Color	Clear	—
Resistivity	$3.5 \times 10^{13} \Omega\text{-cm}$	ASTM D257
Breakdown Voltage	>1 500 V	ASTM D149
Dielectric Strength	1 100 V/mil	
Insulation Resistance	$1 \times 10^{12} \Omega\text{-cm}$	IPC-TM-650 2.5.7.1
Moisture Insulation Resistance	$1 \times 10^{12} \Omega\text{-cm}$	IPC-TM-650 2.6.3.4
Glass Transition Temperature ( $T_g$ )	38 °C	ASTM E1545
Coefficient of Thermal Expansion (CTE)	160 ppm/°C (Prior $T_g$ )	ASTM E831
Service Temperature Range	-65–130 °C	—

# 419E Liquid



## Application Instructions

Read the product SDS before using this product (downloadable at [www.mgchemicals.com](http://www.mgchemicals.com)).

## Recommended Preparation

Clean the substrate with MG #824 99.9% Isopropyl Alcohol, so the surface is free of oils, dust, and other residues.

## Recommended Thinner

When thinning is required, use MG #4352 Thinner 2.

## Brush

This product can be applied by brush for rework or touch-ups. Thinning is not required for most brush applications. Desired coating thickness can be achieved in a single application. Applied coating can be cured immediately.

## Manual Spray Guns

Use a standard fluid nozzle gun with a minimum tip diameter of 0.8–1.0 mm. The settings listed below are recommendations; however, performance will vary with different brands:

Inlet	Air Flow	Air Cap
20–40 psi	10–15 SCFM	8–10 psi

1. Dilute 1-part coating to 1-part thinner (MG #4352 Thinner 2). Adjust ratio if required.
2. Stir the coating gently, but thoroughly.
3. Spray a test pattern to ensure good flow quality.
4. Tilt the board at 45° and spray a thin even coat from a distance of 20–25 cm (8–10 in). Use spray-and-release strokes with an even motion to avoid paint buildup in one spot. Start and end each stroke off the surface.
5. Wait 3 min between coats to avoid trapping solvent.
6. Rotate the board 90° and spray again to ensure good coverage.

7. Apply additional coats until desired thickness is achieved (go to step 3).

8. Let dry for 15 min at room temperature before applying heat cure.

## Dip Coat

Use a Ford or Zahn cup to monitor the viscosity of the coating, as the solvent will evaporate over time.

1. Hang the PCB on a dipping arm.
2. Slowly lower the PCB into a tank and leave immersed in the coating for 2 min to allow penetration.
3. Slowly withdraw the PCB from the tank at a rate of approximately 6" per minute.
4. Let dry for 3 min before applying additional coats or 15 min before heat cure.

## Selective Coating

For higher volume applications, coating can be applied via selective coating equipment. The settings listed below are recommendations and performance will vary with different brands.

Settings	PVA	Nordson Asymtek
Platform	PVA 650	SL 940E
Valve	FCS300-ES	SC 280N
Dilution	1:1 with 4352	4:1 with 4352
Air Pressure	0.5 psi	80 psi
Fluid Pressure	5 psi	25 psi
Dispense Height	10 mm	12.7 mm
Pass Width	5 mm	Not available
Coating Speed	100 mm/s	500 mm/s

## Clean-up

Clean spray system and equipment with MEK or acetone, MG #434.

**Disclaimer:** This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

**MG Chemicals** 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6 ISO 9001:2015 Quality Management System SAI Global File: 004008  
support@mgchemicals.com **North America** +(1) 800-340-0772 **International** +(1) 905-331-1396 **Europe** +44 1663 362888 **30 July 2025 / Ver. 3.0**