

Technical data sheet



Product: 8926 SERIES

Manufacturer: 3M DEUTSCHLAND GMBH

Product group: ELEKTRO

Article group: KLEBEBAND

Download: 27.06.2026

3M THERMALLY CONDUCTIVE INTERFACE TAPE

This data sheet was provided to you by Tewipack Uhl GmbH. The company tewipack Uhl GmbH assumes no responsibility for the topicality and the Accuracy of the information contained. The properties of the products can vary due to various influences such as composition and condition of the Substrate, impurities in or on the substrate, temperature and humidity at the Change storage and environmental conditions during use. Using this product in combination with other material, the customer is responsible for to check through our own tests whether the product is suitable for the planned combination and whether this combination delivers the expected results

Tewipack Uhl GmbH
Industriestraße 15
D-75382 Althengstett

Telephone:
+49(0)7051/9297-0
Fax:
+49(0)7051/9297-99

E-Mail:
info@tewipack.de
Website:
www.tewipack.de

Managing director:
Alexander Uhl,
Michael Uhl
HRB 330424
Amtsgericht
Stuttgart

Bank details:
Sparkasse
Sindelfingen
Pforzheim
Calw
BLZ 666 500
85
Konto 17 787

Commerzbank
Sindelfingen
BLZ 603 400 71
Konto 8 001 166

Vereinigte
Volksbank AG
Böblingen
BLZ 603 900 00
Konto 80 089
003

Postbank
Stuttgart
BLZ 600 100
70
Konto 146
294 708

3M™ Thermally Conductive Interface Tape 8926 Series

Product Description

3M™ Thermally Conductive Interface Tape 8926 Series has 0.20mm, 0.25mm, and 0.50mm thick pressure sensitive adhesive tapes filled with thermally conductive ceramic particles. These products have good converting ability, handing, and re-workability through the introduction of a thin PET carrier. 3M tape 8926 series has a soft acrylic polymer and multiple thickness options to allow for excellent wet-out or conformability to many surfaces. The tape series has good adhesion performance to many substrate types and has excellent dielectric performance.

Product Uses

These products can be used for heat management in electronic devices and for general heat dissipation in devices. They may also be used for bonding/joining parts in electronic products.

Key Features

- Good thermal conductivity
- Excellent dielectric performance
- Low thermal impedance
- Good and reliable adhesion performance to Al and SS
- Vibration damping

Product Construction/Material Description

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Thermally Conductive Interface Tape 8926 Series	
Property	Value
Adhesive type	Soft Acrylic Adhesive
Tape Thickness	0.2mm / 0.25mm / 0.5mm
Tape color	Yellowish White
Filler type	Ceramic Particle
Product Liner	75µm PET Film Liner
Roll length	Standard: 40m (0.20 mm, 0.25mm, and 0.5mm) Custom size can be supplied upon request

Applications

- General heat sink bonding
- IC chip packaging heat conduction
- Printed circuit board
- LED module/board bonding
- Display assembly (e.g. LCD and LED devices)
- COF chip heat conduction
- Mechanical fastening such as clamp, bracket or screw can be used in parallel with this tape.

3M™ Thermally Conductive Interface Tape 8926 Series

Application Techniques

- Bond strength is dependent upon the amount of adhesive to surface contact developed. Firm application pressure helps to develop better adhesive contact and improve bonding strength.
- To obtain optimal adhesion, the bonding surfaces must be clean, dry, and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane. Note: Be sure to follow manufacturer's safety precautions and directions for use when using solvents.
- Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F). Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the product's Certificate of Analysis (COA) that is shipped with the commercialized product.

3M™ Thermally Conductive Interface Tape 8926 Series				
Property	Method*	8926-02	8926-25	8906-5
90° Angle Peel Adhesion Crosshead speed: 508mm/min	ASTM D-3330*			
SUS 304 Test substrate		Unit gram/25.4mm width (N/mm)		
15 min dwell at 23°C	Liner side	1300 (0.5)	1300 (0.5)	1300 (0.5)
	Non-liner side	1300 (0.5)	1300 (0.5)	1300 (0.5)
72h Dwell at 70°C (For reference)	Liner side	2000 (0.77)	2000 (0.77)	2000 (0.77)
	Non-liner side	2000 (0.77)	2000 (0.77)	2000 (0.77)
Dynamic Shear Crosshead speed: 305 mm/min	ASTM D-1002 Initial Adhesion (SUS to SUS)	15 kg/6.25cm ²		
Foam Density		1.6 (+/-0.10) g/cm ³		
Dielectric Strength	ASTM D-149	15 kV/mm		
Thermal Conductivity**	XY direction: Hot wire plane Test Z direction: ASTM D5470	1.5 W/m-K		
Thermal Impedance <i>Imperial Unit</i>		1.31°C-in ² /W	1.35°C-in ² /W	1.50°C-in ² /W
Thermal Impedance <i>Metric Unit</i>		8.49°C-cm ² /W	8.74°C-cm ² /W	9.70°C-cm ² /W
Flammability***	UL94	V-0		
Operating Temperature Range****	3M Test Method	Long Term (Weeks – Months): Up to 80°C Short Term (Hours – Days): Up to 90°C		

*Methods listed as ASTM are tested in accordance with the ASTM method noted

**3M Thermal Conductivity Interface Tape 8926 Series Test Methods:

- 1.5W/m-K in XY direction per Hot wire plane Test method (Test equipment: QTM-500)
- 1.5W/m-K in Z direction tested in accordance with a simplified ASTM D5470 type method (Test equipment: T3ster DynTIM)

*** Flame rating is only valid for the material coated on one side of aluminum plate with minimum 1.0mm thickness and the other side of recognized component (QMTS2) FR-4 laminate at minimum 0.8mm thickness.

**** Note: The end use customer application, design and verification testing will determine the final in use effective temperature range based on each application's environmental conditions.

Storage and Shelf Life

The shelf life of 3M™ Thermally Conductive Interface Tape 8926 Series is 18 months from the date of manufacture when stored in the original packaging materials and stored at 21°C (70°F) and 50% relative humidity.

3M™ Thermally Conductive Interface Tape 8926 Series

Certificate of Analysis (COA)

The 3M Certificate of Analysis (COA) for this product is established when the product is manufactured and is deemed commercially available from 3M. The COA contains the 3M specifications, test methods and test results for the product's performance attributes that the product will be supplied against. Contact your local 3M representative for this product's COA.

This technical data sheet may contain preliminary data and may not match the COA specification limits and/or test methods that may be used for COA purposes.

3M™ Thermally Conductive Interface Tape 8926 Series

Regulatory: For regulatory information about this product, contact your 3M representative.

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product in accordance with all applicable instructions and with appropriate safety equipment, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specifications on the Certificate of Analysis, which is established when the product is manufactured and deemed commercially available and is provided at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement or repair of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by applicable law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: For industrial use only. Not intended, labeled or packaged for consumer sale or use.



Electronics Materials Solution Division

3M Center 223-3S-32
St. Paul, MN 55144
1-800-251-8634 phone
651-778-4244 fax
www.3M.com/electronics

3M is a trademark of 3M Company.
Please recycle.
©3M 2024. All rights reserved.
60-5005-0450-5